

Enfield Routemaster 9610

Chorinated rubber modified road marking paint

Product Data/ Application Instructions

- Resistant to abrasion
- Good medium for high reflectivity
- Chemical resistant
- Fast drying times
- Tested to BS6044 performance standard
- May be applied to most road surfaces
- Skid resistant

Typical Uses

Line marking paint for: Old black top, concrete, wood, brick, paving and certain existing thermoplastic and painted lines. Roads, airport and airfield runways. Car parks, factories and sports facilities.

Overcoating

Can be overcoated with itself if necessary. Before using the product, read the label on the can and consult the material safety data sheet.

Physical Data

Appearance when dry	matt		
Colour	white, yellow, black, red, blue and green		
Components	1		
Volume solids	50 ± 2%		
VOC*			
EC SED 1999/13/EC	296 g/kg	(455 g/l)	
UK PG6/23(92) Appendix 3	343 g/l		
Curing mechanism	solvent release		
	typical	minimum	maximum
Dry film thickness (µm)	175	150	200
Wet film thickness (µm)	350	300	400
(Wet film thicknesses quoted are theoretical for one machine application)			
Theoretical coverage	up to 57 metres of 5 cm		
(at typical dft)	line per litre (188ft of 2 inch line per litre)		
Specific gravity	1.6 kg/l		
Flash point			
(closed cup)	°C	°F	
Enfield Routemaster 9610 ...	54	129	
Amercoat 65	24	75	

* VOC figures are quoted according to both the EC directive 1999/13/EC which are theoretically calculated figures and the UK PG6/23(92) Appendix 3 which are practically determined figures.

Enfield Routemaster 9610

Surface Preparation

BLACKTOP - May be applied to blacktop at applicators discretion, however, Ameron Coatings recommend a sealer coat of Enfield Routemaster 9503 is applied prior to use of Enfield Routemaster 9610.

SYNTHETIC ALL WEATHER SURFACES - Check compatibility prior to use.

EXISTING THERMOPLASTIC - Check compatibility prior to use.

CONCRETE.-.Substrate should be sound and free from laitence.

NOTE - All surfaces must be dry and free of dust, salts, grease and other contaminants immediately before coating.

Application Methods

MACHINE APPLICATION - is recommended in order to obtain the maximum coverage, film thicknesses and consistency of line. Do not thin the coating.

BRUSH - Apply evenly using a clean, well loaded brush; do not attempt to brush out or lay-off the wet coating otherwise correct thickness will not be achieved.

Application Data

Substrate	blacktop, concrete
Application methods	machine, brush
Potlife (at 20°C/68°F)	not applicable
Environmental Conditions	
Relative humidity:	up to 90%.
Surface temperature:	minimum 5°C/41°F
.....	maximum 30°C/86°F

The surface temperature must also be at least 3°C/5°F above the dew point.

Prior to the use of Enfield Routemaster 9610 in hot climates, where surface temperature is likely to exceed 30°C/86°F for long periods, consult your Ameron representative for specific technical advice.

Drying Characteristics

Temperature	20°C/68°F
Touch dry	10 minutes
Hard dry	15 minutes
Full cure	7 days
Overcoating (minimum)	1 hour
Overcoating (maximum).....	-

NOTE: drying and curing times are dependent on air and steel temperature, applied film thickness, ventilation and other environmental conditions. Times are shorter at higher temperatures and longer at lower temperatures

Thinner	normally not necessary
Cleaner	Amercoat 65

Enfield Routemaster 9610

Mixing

Stir thoroughly before use until the product is uniform throughout.

Shipping Data

Shipping weight..... approx. 35 kg (20l)
approx. 9 kg (5l)

Pack size 5 and 20 litres

Shelf life 1 year when stored indoors in
unopened, original containers at 5
to 35°C (41 to 95°F).

Reflectivity To reflectorise, apply Ballotini glass
beads 9618 to the wet film at a rate
of 400g per square metre.

Enfield Routemaster 9610

Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

Warranty

Ameron warrants its products to be free from defects in material and workmanship. Ameron's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at Ameron's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to Ameron in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify Ameron of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

Ameron makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall Ameron be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by Ameron, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

Ameron's liability on any claim of any kind, including claims based upon Ameron's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim.

In no event shall Ameron be liable for consequential or incidental damages.

Due to Ameron's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the Ameron Performance Coatings & Finishes website at www.ameroncoatings.com

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.

Performance Coatings & Finishes

Ameron B.V.

Tel +(31) 345 587 587
www.ameron-bv.com

Ameron International Corporation

Tel +(1) 678 393 0653
www.ameroncoatings.com

Ameron (Australia) Pty Ltd.

Tel +(61) 2 9421 8000
www.ameron.com.au

Ameron (New Zealand) Ltd.

Tel +(64) 9 573 1620
www.ameron.co.nz

