

COO-VAR TEAK OIL DATA SHEET

DESCRIPTION: Coo-Var Siliconised Teak Oil is a blend of natural oils and silicone derivatives which enhance, preserve and restore the appearance of teak and other hardwoods. It has a good degree of resistance to water and can be used inside or outside. The oil takes better to hardwood than traditional varnish's.

RECOMMENDED USE: Coo-Var Siliconised Teak Oil is used on teak and other hardwoods, ideal for use on outdoor furniture.

AVAILABILITY: 0.5 litre, 1 litre, 2.5 litre

FINISH: Oiled

COLOUR: Clear

TYPICAL S.G. (SPECIFIC GRAVITY): 0.86 @ 20C

VOLUME SOLIDS: 34%

EXPECTED SPREADING RATE: 7sq.m / litre

Average figure dependant on the porosity of the wood.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY: Thin Liquid

FLASH POINT: Above 30C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch Dry: 8 hours @ 20C

Hard Dry: 24 hours @ 20C

Full hardness: N/A

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME: 16 Hours or overnight

VOC CONTENT: Max 514 g/litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Brush or Cloth,

Use Coo Var Thinner 14 for cleaning

Recoat interval 16 hours or overnight.

SURFACE PREPERATION: All surfaces should be clean, dry, sound and free from contaminants.

Ensure the surface is left to dry for 1-2 weeks. Use sandpaper to remove any unwanted old coating or paint.

MIXING INSTRUCTIONS: Mix well before use

APPLICATION INSTRUCTIONS: As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

SUBSEQUENT COAT: Coo var siliconised Teak oil

REMARKS: Apply as a flood coat, work well into grain, taking particular care at "end" grains.

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specificaton. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01462 421333