

PRODUCT DATA SOLVENT-FREE, HIGH-BUILD EPOXY SYSTEM 5500

DESCRIPTION

RUST-OLEUM® Solvent-free, High-Build Epoxy System 5500 is based on two-component epoxy resins.

RECOMMENDED USES

RUST-OLEUM Solvent-free, High-Build 5500 System is designed for application on concrete and masonry and can also be used on blasted steel.

RUST-OLEUM 5500 System is primarily intended for roller application and may also be applied by brush for small areas or touch-up only.

A two coat RUST-OLEUM 5500 System assures appropriate protection when contacted with many food products, chemicals (see chemical resistance guide), frequent chemical cleaning or high humidity and moisture conditions.

RUST-OLEUM 5500 System can be applied directly on properly cleaned, sound mineral substrates, sound, well prepared previous Epoxy coatings; porous substrates should be primed with RUST-OLEUM 5401 Impregnation Primer; very dense substrates, like ceramic tiles, should be primed with RUST-OLEUM Super Adhesive 3333.

RUST-OLEUM 5500 System can be applied directly on blasted steel or blasted galvanised steel; if required primed with RUST-OLEUM 9170/9180 Primer.

RUST-OLEUM 5500 System is approved for direct food contact in various European countries.

RUST-OLEUM 5500 System is classified Class 1 Surface Spread of Flame according BS 476; part 7 : 1987.

TECHNICAL DATA

| | |
|-----------------------------|---|
| Appearance: | High gloss |
| Colour: | See colour card |
| Density: | 1.33 kg/ltr. ± 0.03 (mixed product) depending on colour 5510 Clear is 1.10 kg/ltr. |
| Solids Content: | 100% by volume (mixed product) |
| Viscosity: | > 140 KU / Krebs Stormer Units at 20°C (mixed product) |
| Recommended film thickness: | 150 µm dry, equals 150 µm wet |
| VOC-content: | 0 g/l |

| Drying times | 20°C/50% r.h. | 10°C/60% r.h. | 30°C/50% r.h. |
|-----------------|-----------------------------------|-----------------------------------|-----------------------------------|
| To touch: | 24 hours | 36 hours | 16 hours |
| To recoat: | After 24 hours Within 72 hours | After 36 hours Within 96 hours | After 16 hours Within 72 hours |
| Full hardness: | 10 days | 3 weeks | 7 days |
| For immersion*: | 14 days | 4 weeks | 10 days |

*) Actual curing time depends on the composition of the content (substance).

Heat resistance: 150°C (dry heat) at elevated temperatures discoloration may occur.
50°C (immersion or wet heat).

Coverage

| | |
|--------------|--|
| Theoretical: | 6.7 m ² /l at 150 µm dry |
| Practical: | Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. |

SURFACE PREPARATION

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A

11, Rue Jules Verne, B.P. 39
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 5D, Alexandra Way
Ashchurch B. Centre,
Tewkesbury, Gloucestershire
GL20 8NB, United Kingdom
T +44 (0)1684 273 333
F +44 (0)1684 273 331
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Via Mazzetta 36, 13856
Vigliano Biellese BI, Italia
T +39 015 8122 160
F +39 015 8122 161
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA SOLVENT-FREE, HIGH-BUILD EPOXY SYSTEM 5500

Concrete and masonry: New concrete or masonry should dry and cure for at least 30 days before applying the coating system.

Remove laitance, loose and unsound concrete or deteriorated coatings preferably by abrasive blasting and repair surface defects with RUST-OLEUM Concrete Repair Mortar 5403 or Epoxy Putty 5412. Very dense and smooth concrete should be abrasive blasted or primed with RUST-OLEUM Super Adhesive 3333.

Steel: Remove loose rust, rust scale and deteriorated coatings by abrasive blasting to Sa 2½ (ISO 8501-1 : 1988), blast profile max. 100 µm.

For immersion purposes, prepare to Sa 3 (ISO 8501-01 : 1988), blast profile max. 75 µm.

DIRECTION FOR USE

These products are supplied in premeasured 'units' consisting of one can of pigmented base-material and one can of activator (5501). Stir individual components thoroughly before mixing them together. Add activator to base material and mix thoroughly with a low speed mixer.

Practical application times for a 4 ltr. mix:

| Material temperature | Time | Pot-life (incl. induction) |
|----------------------|------------|----------------------------|
| 20° | 15 minutes | 60 minutes |
| 15° | 30 minutes | 90 minutes |
| 10° | 1 hours | 2 ½ hours |

APPLICATION & THINNING

Brush: Thinning not recommended.
Use natural bristles, long hair brushes.

Roller: Thinning not recommended
Use medium nap, 12 mm, perlon or polyester rollers.
For textured surfaces use long nap 14-18 mm rollers.

Cleanup: Use RUST-OLEUM Thinner 160.
Preferably use disposable brushes and/or rollers.

APPLICATION CONDITIONS

Temperature of material between 10 and 20°C, air and substrate between 10 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

REMARKS

Maximum dry film thickness per coat: 300 µm dry, equals 300 µm wet. Before using in direct contact with food the cured 5500 coatings shall be washed with a 2% acetic acid or citric acid solution, followed by flushing with fresh water. In time the product can show some yellowing. Apply the coating in strokes in one direction; do not use a cross-lap technique. Do not try to brush out the coating; lay it on thickly.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A

11, Rue Jules Verne, B.P. 39
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 5D, Alexandra Way
Ashchurch B. Centre,
Tewkesbury, Gloucestershire
GL20 8NB, United Kingdom
T +44 (0)1684 273 333
F +44 (0)1684 273 331
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Via Mazzetta 36, 13856
Vigliano Biellese BI, Italia
T +39 015 8122 160
F +39 015 8122 161
info.it@ro-m.com
www.ro-m.com