

PRODUCT DATA

Epoxyshield® 5300 MAXX

DESCRIPTION

Epoxyshield® 5300 MAXX is a user friendly and easy to apply water-based 2 component epoxy garage floor coating with an ultimate adhesion and durability. The product has an excellent wear, impact and abrasion resistance like foot and vehicle traffic. Resists chemicals and standing water. Epoxyshield® 5300 MAXX can be used in combination with decorative chips or an anti slip additive.

RECOMMENDED USES

Epoxyshield® 5300 MAXX can be applied on concrete floors, which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a curing compound, which will prevent a good adhesion. Epoxyshield® 5300 MAXX can also be applied on old good adhering coatings.

Epoxyshield® 5300 MAXX Additives:

- Epoxyshield® Antislip Additive (200.0.7) gives an excellent anti slip finish when mixed with Epoxyshield® 5300 MAXX.
- Epoxyshield® Decorative Chips (505.0.43) are specially designed for use in combination with Epoxyshield® 5300 MAXX. The chips adhere permanently on the floor when they are sprinkled in the wet coating. They give a decorative finish and will also mask dirt and rugosity.

TECHNICAL DATA

Appearance: Gloss
Colour: Silver Gray
Density: Base: 1.32 kg/ltr
Activator: 1.13 kg/ltr
Solids Contents: Base: 54.5% by volume
Activator: 91.0% by volume

VOC-content: 53 g/l max.
Ready-to-use mixture: 53 g/l max.
Category: A/j
EU Limit values: 140 g/l (2007) / 140 g/l (2010)

Drying times bij 20°C/50% r.v.
To handle: 16 hours (suitable for light foot traffic)
To recoat: 48 hours (suitable for normal foot traffic and heavy items)
Full hardness: 7 days (suitable for vehicle traffic)

Induction- and application time

Allow the mixed products to stand after mixing.

	15-20°C	21-25°C	26-30°C
Start brushing:	After 30 minutes	After 10 minutes	Direct
Start rolling:	After 45 minutes	After 15 minutes	After 5 - 15 minutes
Total application time (potlife):	2 hours	1½ hours	1 hours

Remark

Since the application time is only 1 - 2 hours (depending on temperature) it is advisable to apply the product with 2 persons. Have 1 person begin trimming edges and have another person begin rolling out the floor as specified.

Rust-Oleum Netherlands B.V.
Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.
Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.
Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA

Epoxyshield® 5300 MAXX

Coverage

Approx. 7 m²/l depending on the substrate and application method. In general 1 coat is sufficient.

SURFACE PREPARATION

Repair any holes or cracks with EpoxyShield concrete repair products. If the floor is previously painted, remove any loose paint by sanding and scraping. Remove oil and grease using a scrub brush and EpoxyShield cleaner/degreaser. Rinse thoroughly with fresh water afterwards. Remove all water and allow to dry completely. Wipe your fingers over the clean, dry floor. If you see any dust or powder, repeat the rinsing until the floor is clean. Wipe your fingers over the clean, dry floor. If you see any dust or powder on your fingers, repeat the rinsing and scrubbing until the floor is clean.

DIRECTION FOR USE

Pour the contents of A into B and stir thoroughly for at least 3 minutes. Allow mixed product to stand (see table) before rolling the coating on to the surface. Do not leave container in direct sunlight. Mix again before applying.

The product must be used within 1 to 2 hours of initial mixing (pot life, see table). This time decreases at higher temperatures.

Do **not** mix Paint Chips with Epoxyshield® 5300 MAXX.

APPLICATION & THINNING

After the full 60 minutes use a paint roller (20 cm) to apply an even coat of Epoxyshield® 5300 MAXX onto the surface. Apply in sections of 1,5 x 1,5 m so that Epoxyshield® Decorative Chips can easily be scattered on the freshly coated surface. Maintain a wet edge to prevent lap marks and gloss differences. Sprinkle the decorative paint chips onto the wet film (note: this step may be skipped if chips are not desired. This will not affect the performance of the coating). Immediately continue to coat the next section (note: fresh paint can be applied over the loose chips that lay outside the previously painted area). Only one coat is necessary.

Cleanup:

Wash all tools and equipment immediately with warm water and mild detergent. Allow any unused product to harden in the container and discard according to local regulations.

APPLICATION CONDITIONS

Apply when air (ambient) temperature is 15-35°C and relative humidity is below 80%. Concrete floors take a long time to warm up; make sure the previous day has also been at least 15°C prior to painting. Minimum floor temperature for painting is 13°C. Painting in mid-afternoon ensures the best cure.

SAFETY

Avoid contact with skin and eyes. For skin contact, wash affected area with soap and water and rinse well. First aid: in case of contact with eyes, flush with cold water for 15 minutes. If swallowed, do not induce vomiting. Drink 1-2 glasses of water or milk. Contact a physician immediately. Keep out of reach of children. Do not take internally.

Consult for further information the Safety Data Sheet and the Safety Information printed on the can.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA

Epoxyshield® 5300 MAXX

REMARKS

To ensure best performance, DO NOT PAINT IF THE FOLLOWING CONDITIONS EXIST:

- 1) Sealed concrete: dripping a small amount of water onto the surface. If the water beads, a sealer is present and paint may not adhere properly.
- 2) Moisture in the concrete: apply a sheet of plastic (e.g. garbage bag) to the floor. Tape down the edges and allow to set for 24 hours. If water droplets appear on the inside of the plastic or if concrete appears wet (darker in color), moisture is trapped in the concrete.
- 3) Loose concrete or concrete dust: if the concrete is loose, chipping or has concrete dust present, the coating will not perform properly unless all loose material and dust is removed and damaged areas are repaired.
- 4) Floors treated with a levelling mortar or on anhydride floors.

SHELLIFE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com