

PRODUCT DATA

COMBICOLOR® WROUGHT IRON 7300

DESCRIPTION

RUST-OLEUM® CombiColor Wrought Iron 7300 coating is primer and topcoat in one, based on an alkyd resin, providing good drying properties at low temperatures. The product contains rust-inhibitive pigments and is lead- and chromate free.

RECOMMENDED USES

RUST-OLEUM CombiColor Wrought Iron 7300 should be applied on bare, manually derusted or with CombiPrimer Anti-Corrosion 3369/3380 primed steel. CombiColor Wrought Iron is intended for brush and roller application and can also be applied by air spray.

RUST-OLEUM CombiColor Wrought Iron 7300 offers corrosion protection in a light industrial environment.

For metal structures in a more aggressive industrial environment, prior application of a RUST-OLEUM CombiPrimer Anti-Corrosion 3369/3380 is recommended.

TECHNICAL DATA

Appearance:	Wrought Iron
Colour:	7313 green - 7319 black
Density:	1.36 kg/l
Solids Content:	48.0% by volume
Viscosity:	105 - 115 KU / Krebs Stormer Units at 20°C
Recommended film thickness:	50 µm dry, equals 104 µm wet
VOC-content:	400 g/l

Drying times	20°C/50% r.h.	10°C/60% r.h.	30°C/50% r.h.
To touch:	2 hours	3 hours	1½ hours
To handle:	8 hours	16 hours	6 hours
To recoat:	After 16 hours	After 24 hours	After 8 hours
Full hardness	7 days	14 days	5 days

Heat resistance: 90°C (dry heat), at elevated temperatures discoloration may occur.

Coverage

Theoretical:	10.3 m ² /l at 55 µm dry, depending on colour.
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove oil, grease and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 3 (ISO 8501-1 : 1988), light blast cleaning or sanding. Sand intact coatings to roughen the surface slightly.

The surface must be clean and dry during application. Galvanised, Zinc and Aluminium surfaces have to be primed first with CombiPrimer Tack Coat 3302.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush: Up to 10 vol. %; RUST-OLEUM Thinner 7301.
Use natural bristles, long hair brushes.

Roller: Up to 10 vol. %; RUST-OLEUM Thinner 7301.
Use short nap, poly-amid (Perlon) 6-12 mm rollers.
Roller application may require 2 coats to achieve recommended dry film thickness

Rust-Oleum Netherlands B.V.
Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A
Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A
11, Rue Jules Verne, B.P. 39
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Unit 5D, Alexandra Way
Ashchurch B. Centre,
Tewkesbury, Gloucestershire
GL20 8NB, United Kingdom
T +44 (0)1684 273 333
F +44 (0)1684 273 331
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.
Via Mazzetta 36, 13856
Vigliano Biellese BI, Italia
T +39 015 8122 160
F +39 015 8122 161
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA

COMBICOLOR® WROUGHT IRON 7300

Air-atomised spray: 10-25 vol.%; RUST-OLEUM Thinner 7301.
Gravity cup and pressure cup.
Tip size: 1.0 -1.5 mm.
Atomising pressure: 2 - 4 bar.

Cleanup: Use RUST-OLEUM Thinner 7301 or RUST-OLEUM Thinner 160.

APPLICATION CONDITIONS

Temperature of air, substrate and coating material between 5° and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

REMARKS

Maximum dry film thickness per coat: 75 µm dry, equals 155 µm wet.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A

11, Rue Jules Verne, B.P. 39
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 5D, Alexandra Way
Ashchurch B. Centre,
Tewkesbury, Gloucestershire
GL20 8NB, United Kingdom
T +44 (0)1684 273 333
F +44 (0)1684 273 331
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Via Mazzetta 36, 13856
Vigliano Biellese BI, Italia
T +39 015 8122 160
F +39 015 8122 161
info.it@ro-m.com
www.ro-m.com