

BIOSAN

AQUA PLUS

TECHNICAL DATA SHEET

DATE : 01/05
ISSUE : 03
NUMBER : **TE-113**

► DESCRIPTION

Bactericidal 2-component water dilutable epoxy coating.

► APPLICATION

For the interior coating of walls and ceilings in areas where controlled hygienic conditions are of essential importance and where high abrasion resistance is needed.

► FEATURES

Very hard - exceptional abrasion resistance - resistant to oils and solvents.
Solvent free, almost odourless and easy to clean, helps to maintain a hygienic environment.

► TECHNICAL DATA

Binder	:	Base : epoxy-amine adduct Activator : bisphenol A-F resin
Finish	:	semi-gloss
Gloss (60°)	:	± 60
Colour (s)	:	white + mixing machine pastel colours
Solids content (ASTM, D1644/a)	:	in volume : 48 – 50 % in weight : 64 – 66 %
Density (ASTM, D1475, 20°C)	:	± 1,45 g/cm ³ (mixture)
VOC-content (Volatile Organic Compounds)	:	0 g/l
Consumption	:	approx. 7 m ² /l per coat
Thickness wet film	:	± 140 micron (cons.: 7 m ² /l)
dry film	:	± 70 micron (cons.: 7 m ² /l)
Drying times	:	* dustfree : 3 hours
(for t° 20°C)	:	* recoatable : 24 hours
(for R.H. 60%)	:	* full cure : 7 days
Flashpoint (DIN53213)	:	not flammable
Surface Spread of Flame (BS476 Part 6 & 7)	:	rated Class 0 to the UK Building Regulations
Miscellaneous items	:	1. At lower temperatures (8 – 10°C), this product can only be recoated after ± 48 hours. 2. Potlife after mixing base and activator : 2 hours.

► INSTRUCTIONS FOR USE

Ambient conditions	:	minimum 8°C and maximum 80 % R.H.
Dilution	:	water
Cleaning tools	:	water
Airless	:	Nozzle : 021 - 023 Pressure : 220 bars 1 st coat : dilute with 10 % water 2 nd coat : dilute with max. 10 % water
Conventional spray-gun	:	no
Brush	:	possible
Roller	:	Dilute 1 st coat with max. 10 % water. Apply 2 nd coat undiluted.
Particularities	:	<ol style="list-style-type: none">1. In order to become a solid gloss finish, please respect the consumption quantities of the second layer, this means that a tin of 5 l has to be applied on a surface of approx. 35 m².2. Always provide a good air ventilation; so even when it rains, windows and doors have to be opened wherever possible.3. The 2 components must be mixed <u>under mechanical agitation</u>.4. The use of Biosan products does not exclude the necessity to clean and disinfect on a normal and regular basis.

► PREPARATION OF THE SUBSTRATE

The substrate should be dry and clean, free from ascending humidity and sufficiently coherent (tensile strength min. 6 kg/cm²).

Biosan Aqua Plus can be applied directly on most mineral substrates (f.i. old concrete, tiles, glass, etc.).

Curing compounds in case of poly-concrete have to be removed by means of grit blasting.

On new concrete or non porous concrete, remove cement grout by grit blasting or treatment with Rust-Oleum Surfa Etch 108.

Porous substrates shall be impregnated with Biosan Aqua Plus diluted with 10 to 20 % water.

Biosan Aqua Plus may not be applied on a flexible paint coat or a moving substrate.

► ADDITIONAL INFORMATION

Transport codes	:	see MSDS
Packing	:	5 l
Storage stability	:	At least 24 months, provided the original can is properly sealed and kept in a cool, dry and frostfree place.
AFNOR Classification	:	Group I, class 9g

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, expressed, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.

"As for the precautions of use, hygiene and safety, please consult our Material Safety Data Sheets - available on request at our Technical Service".