

TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- MARINE UNDERCOAT

REFERENCE:- F/158/1

COLOUR:- WHITE

FINISH:- MATT

TYPE:- MODIFIED ALKYD

TYPICAL SG:- 1.41 @ 20°C

TYPICAL VISCOSITY:- 3.5 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 66.2% BY WEIGHT
40.0% BY VOLUME

FLASH POINT:- ABOVE 32°C

RECOMMENDED THINNERS:- WHITE SPIRIT OR TURPS SUBS

APPLICATION:- BRUSH, ROLLER OR SPRAY

*COVERAGE GUIDE:- 10 SQ. METRES/LITRE

*DRYING TIME:- SURFACE DRY - 2 HOURS
THROUGH DRY - 12 HOURS

HEALTH & SAFETY:- SEE SHEET HSD 'A'

*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.

Teamac® Paints

**MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL
COATINGS**

Teal & Mackrill Limited,
Lockwood Street, HULL. HU2 OHN
Telephone: 01482-320194 Fax: 01482-219266