



Technical Data Sheet

Blackfriar Professional Anti-Slip Floor Paint

An attractive, tough, durable and high opacity floor coating. Contains special aggregates for outstanding slip resistance. Suitable for indoor and outdoor use on concrete, cement, wood, metal and stone surfaces.

Performance characteristics –

- Resists grease, oil and weak solutions of acid and alkali.
- Contains special slip-resistant aggregates.
- Ideal for light industrial and domestic floors.
- Indoor and outdoor use.
- Brush or roller application.

Preparation

Ensure the surface to be painted is sound, clean, dry and free from grease or any substance liable to give adhesion problems. Scrape off any old or flaking paint until you have a firm surface. Special attention should be given to areas under cars to ensure all oil, grease, dirt and road salt is removed. New concrete must be left for at least 6 months before applying Blackfriar Professional Anti-Slip Floor Paint.

Application

Stir thoroughly before use. Apply with a brush or roller working the paint in any surface imperfections. On bare or new surfaces first apply Blackfriar Professional Solvent Based Floor Sealer followed by 1-2 coats of Blackfriar Professional Anti-Slip Floor Paint. On previously painted surfaces apply 1-2 coats as required. Blackfriar Professional Anti-Slip Floor Paint is not suitable for use over PVC, thermoplastic tiles, quarry tiles, asphalt floors or granolithic concrete. Do not apply it on concrete surfaces treated with alkali containing liquids, areas subjected to rising damp or areas treated with PVA bonding solutions. If concrete floors are very smooth then pre-treat with Blackfriar Professional Acid Etch followed by Blackfriar Professional Solvent Based Floor Sealer prior to applying 1-2 coats of Blackfriar Professional Anti-Slip Floor Paint. Surfaces are slippery when wet. To ensure slip resistance the floor must be kept dry when in use. The use of

protective mats will help preserve the surface under tyres.

Coverage Rate

6-10m²/litre per coat. Two coats recommended.

Drying Time

4-6hrs@20°C. Allow to dry for a minimum of 16hrs @20°C between coats. Allow to dry for a minimum of 48hrs@20°C before subjecting to heavy traffic. Full cure is achieved in 5-7 days@20°C.

Clean Up

Remove as much product from application equipment as possible before washing with Blackfriar Brush Cleaner or White Spirits. Do not empty into drains or watercourses. Some local authorities have special facilities for the disposal of waste coatings.

Danger

Contains: Naphtha (petroleum), hydrotreated heavy

Flammable liquid and vapour.

May cause drowsiness or dizziness.

Causes damage to organs through prolonged or repeated exposure if inhaled.

Keep out of reach of children.

Read label before use. If medical advice is needed, have product container or label at hand.

Keep away from heat, sparks, open flames and hot surfaces. - No smoking.

Use only outdoors or in a well-ventilated area.

Do not breathe vapour. Call a doctor if you feel unwell.

Store in a well-ventilated place. Keep cool. Store locked up.

Dispose of contents and container in accordance with all local, regional, national and international regulations.

EU limit value for this product (Cat IIA/i): 600g/l (2007) 500g/l (2010.) This product contains a maximum of 325g/l VOC.

Whilst every effort is made to ensure the accuracy of colour,
due to limitations of the print process, colour / finish shown
is for guidance only.