

TEST RESULTS

Pronto 450:004

ProTect Vinyl Sheen

BS EN 2409 2013 Cross - Cut Test (Plus Tape pull off Test)



No detachment

BS EN ISO 15118 2011 Scratch Test



Pass at 1.5 Kg

BS EN ISO 6272-1 2011 Falling Weight test



1kg @ 1 Metre Direct Impact and Reverse Impact
Direct impact: No detachment or splitting of coating on circumference of impact

Reverse impact: Coating detachment only at peak of impact. No splitting or detachment of coating on circumference of impact.

TEST RESULTS

Pronto 450:004

ProProtect Vinyl Sheen

BS EN ISO 1519 2011 Bend Test Cylindrical Mandrel



3mm Mandrel: No split or detachment of coating on bend.

BS EN ISO 9227 2012 Corrosion Tests in Artificial Atmospheres – Salt Spray



500 Hours. No blistering of panels or creep from scribe.

Conformity

ISO 12944-5-2007, Categories C2, C3 and C4 for Vinyl Chloride Copolymers (PVC) when used as part of a system.

ISO 12944-5-2007, Categories C5I and C5M for Vinyl Chloride Copolymers (PVC) when applied over hot dip-galvanised steel.