

Guide To Quantities of Rustoleum Coatings Required For 10 & 15 Year Warranty On Roofing and Vertical Cladding Systems

Noxyde Warranty

For all warranty systems you will require the use of AMW Wash to remove algae and any other green growth, followed by a clean and degrease with Rustoleum ND14. These quantities will be determined by condition of the substrate.

To qualify for the warranty, a Plastisal roof will need to be a minimum area 500m². A site visit will be required arranged by Promain UK Limited and a work card will need to be completed before work commences, allow a minimum of 3 weeks before work commences for this to be arranged.

Allow approximately 30% extra material for stripe coat, edge lap repair and including additional area for corrugated profile.

Materials Required For 10 Year Noxyde Warranty

Roofs 2 coats at 400 gms per m²
Verticals 2 coats at 300 gms per m²

Materials Required For 15 Year Noxyde Warranty

Roofs 2 coats at 500 gms per m²
Verticals 2 coats at 400 gms per m²



Noxyde & Metal Cladding Topcoat Warranty

Materials Required For 10 Year Decorative Warranty for Vertical Cladding

1 coats at 400 gms per m² Noxyde
1 coat of Metal Cladding Topcoat at 8m² per litre

Pegarust Warranty

Materials Required For 10 Year Pegarust Warranty

Roofs 2 coats at 2.9 m² per litre per coat
Verticals 2 coats at 2.9 m² per litre per coat



All of these systems can be overcoated with Rustoleum Metal Cladding Topcoat to provide in excess of 30,000 colours.

Date of Issue 12/01/2018