

PRODUCT DATA

VERNAC GLOSS

DESCRIPTION

Solvent based acrylic varnish.

MAIN PROPERTIES

Completely colourless - transparent - high weather resistance - excellent flexibility - alkali-resistant - non-yellowing.

RECOMMENDED USES

Protection of non-ferrous metals; renovation of transparent skylights (except for polycarbonate). Do not apply Vernac Gloss as floor varnish or on places that are subject to mechanical pressure.

TECHNICAL DATA

Appearance:	Glossy (gloss 60°: > 90%)
Colour:	Colourless
Density:	0,96 - 0,98 g/cm ³
Solids Content:	In volume: 40 - 43% In weight: 47 - 49%
Recommended film thickness:	Wet film: ± 100 micron (consumption: 10 m ² /l) Dry film: ± 42 micron (consumption: 10 m ² /l)
Flashpoint:	> 39°C
VOC-content:	499 g/l max.
Ready-for-use mixture:	499 g/l max.
Category:	A/i
EU Limit values:	600 g/l (2007) / 500 g/l (2010)

Drying times	20°C/50% r.h.
To touch:	1 hour
To handle:	1½ hours
To recoat:	4 hours
Full hardness:	1 day

Coverage

Theoretical:	10 - 15 m ² /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The substrates must be completely dry and clean.

On metals, it is necessary to remove old varnish layers (with Rapid Super, for instance) and oxidation traces (with a polish, for instance). Clean afterwards with a cloth soaked in Thinner 22.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush:	All types.
Roller:	Mohair paint roller or shorthaired perlon roller.
Cleanup:	Thinner 22

Rust-Oleum Netherlands B.V.
Bosk 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60038
95322 St-Leu-la-Foret Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 80
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2478 717 329
F +44 (0)2478 718 930
info@rust-oleum.eu
www.rust-oleum.eu

PRODUCT DATA

VERNAC GLOSS

APPLICATION CONDITIONS

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80%.
No condensation during drying time. Low temperatures and/or high relative humidity will extend the drying time. The temperature of the substrate should be 3°C above dew point.

REMARKS

- 2 - 3 coats for outside works.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.
Brak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60038
95322 St-Leu-la-Foret Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 80
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info@rust-oleum.eu
www.rust-oleum.eu