

TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- HAMMERCOTE SMOOTH SATIN

REFERENCE:- G126/2

COLOUR:- BLACK

FINISH:- SATIN

TYPE:- MODIFIED ALKYD

TYPICAL SG:- 1.14@ 20°C

TYPICAL VISCOSITY:- 8.0 – 10.0 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 59% BY WEIGHT
46% BY VOLUME

FLASH POINT:- 23°C

RECOMMENDED THINNERS:- V/607/15 FOR BRUSH USE,
CLEANING ETC.
V/607/16 FOR SPRAYING (10%
ADDITION AS START GUIDE,
AMOUNT NECESSARY BEING
DEPENDANT UPON TYPE OF
EQUIPMENT AND USER)

APPLICATION:- BY BRUSH OR SPRAY

*COVERAGE GUIDE:- 10 SQ. METRES/LITRE

*DRYING TIME:- SURFACE DRY - ½ HOUR
THROUGH DRY - 6 HOURS

USES:- AS A FAST DRYING FINISH
GIVING A HARD DURABLE FILM.
THE USE OF A PRIMER
ENHANCES ADHESION TO METAL
THE RECOMMENDED TYPE IS
WATER BASED ALL METALS
PRIMER

HEALTH & SAFETY:- SEE SDS 11315

*BY BRUSH TO A DRIED FILM THICKNESS OF 40 - 45 MICRONS AT 20°C.

COO-VAR

PAINTS, PRIMERS & SPECIALISED COATINGS

Ellenshaw Works, Lockwood Street, HULL. HU2 0HN
Telephone : 01482-328053 Fax: 01482-219266