

RUST-OLEUM
— INDUSTRIAL —



EPOXYSHIELD® CONCRETE REPAIR MORTAR

For leveling and repairing cracks and holes



- Traffic allowed after 24 hours
- Recoatable after 48 hours
- 10 kg (1-component) – 0.4 m²
- Sandable to a smooth finish

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

EPOXYSHIELD® CONCRETE REPAIR MORTAR

DESCRIPTION

Powdered repair product on cement base and resins for inside and outside use. For leveling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

RECOMMENDED USE

For levelling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

TECHNICAL DATA

Density: 1,6
Mixing Ratio: Powder : Water = 5kg : 1L

DRYING TIMES AT 20°C/RH 50%

Dry to recoat: 2 days
Fully cured: 1 month

RECOMMENDED WET FILM THICKNESS

2 cm (cons.: 25 kg/m²)

RECOMMENDED DRY FILM THICKNESS

2 cm (cons.: 25 kg/m²)
Maximum 0,4 m² per 10 kg (film thickness 2 cm).

SURFACE PREPARATION

On bare substrate: clean with steel brush or sand blaster. The substrate must be solid and free from dust, oil and grease. Porous substrates must be moistened first. Metal parts are to be treated with an anti-rust primer (Combiprimer 3369/3380 or Hard Hat 2169/2182).

APPLICATION CONDITIONS

Apply at a temperature of min. 5°C.

APPLICATION & THINNING: RAKE/TROWEL

Mixing & Thinning: Mixing ratio: Approximately 5 parts of powder to 1 part of water (2 litres of water for the entire 10 KG). Fill the container with the water. Add the dry mortar to the water whilst stirring. Mix water and powder thoroughly to a thick smooth, lump-free substance. Add some water to your liking if the mortar is too dry.

Application: Apply the product with the included trowel or spatula up to a maximum layer thickness of 2 cm. Wet the trowel to smooth out any trowel marks or irregularities. After 48 hours the surface can be sanded using a rough sandpaper (P120) to obtain a smooth end result.

CLEANING OF EQUIPMENT / SPILLS

Water

REMARKS

The mortar can now be over coated with EpoxyShield® coatings or other non-alkyd paints like Epoxies, Acrylics, etc.

If thicker layers are necessary (> 2 cm) the mortar can be mixed with kiln dried quartz sand. Mixing ratio: 1 volume part mortar plus 0,3 to 0,5 volume parts of kiln dried quartz sand (0 - 4 mm).

SAFETY DATA

VOC level: 0 g/l
Flashpoint: Not flammable
Remarks regarding safety: Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

1 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 12/04/2018

Available colours & pack sizes : Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer : The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu