

# NU-KLAD™ AQUA

## DESCRIPTION

Two-component, waterborne epoxy floor coating

## PRINCIPAL CHARACTERISTICS

- Suitable for industrial areas with occasional light traffic
- Fast return to service
- Good abrasion resistance
- Can be overcoated with a polyurethane topcoat for aesthetic durability
- Suitable for use with anti-skid
- A thinned version can be used as a primer for application directly on concrete

## COLOR AND GLOSS LEVEL

- A wide range of colors
- Flat

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
<b>Number of components</b>	Two
<b>Mass density</b>	1.3 kg/l (10.8 lb/US gal)
<b>Volume solids</b>	53 ± 2%
<b>VOC (Supplied)</b>	Directive 1999/13/EC, SED: max. 5.0 g/kg max. 6.0 g/l (approx. 0.1 lb/US gal)
<b>Recommended dry film thickness</b>	60 - 100 µm (2.4 - 4.0 mils)
<b>Theoretical spreading rate</b>	8.8 m <sup>2</sup> /l for 60 µm (354 ft <sup>2</sup> /US gal for 2.4 mils) 5.3 m <sup>2</sup> /l for 100 µm (213 ft <sup>2</sup> /US gal for 4.0 mils)
<b>Overcoating Interval</b>	Minimum: 5 hours Maximum: 21 days
<b>Dry to walk on</b>	5 hours
<b>Full cure after</b>	7 days
<b>Shelf life</b>	Base: at least 12 months when stored cool and dry Hardener: at least 6 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

# NU-KLAD™ AQUA

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions of concrete for thinned version

- Dried for at least 28 days in good ventilation conditions
  - Moisture content should not exceed 4.5%
  - Concrete must be sound, dry, free from laitance and any contamination
  - Rough surface; eventually abraded by power tool or diamond abrading tool
- 

### Coated concrete

- Existing sound coating systems; sufficiently roughened, dry and cleaned
  - To ensure compatibility, rub the existing coating with a cloth with Xylene or MEK for 10 seconds, and remove existing coatings if dissolving occurs
  - Rough surface; eventually abraded by power tool or diamond abrading tool
- 

### Substrate temperature and application conditions

- Ambient temperature during application and curing should be between 10°C (50°F) and 30°C (86°F)
  - Relative humidity during application and curing should not exceed 75%
  - Substrate temperature during application and curing should be between 10°C (50°F) and 30°C (86°F)
  - Substrate temperature during application should be at least 5°C (7°F) above dew point
- 

## SYSTEM SPECIFICATION

### Standard system

- NU-KLAD AQUA: 2 x 60 µm (2.4 mils) on top of primed concrete
- 

### Anti-skid system

- NU-KLAD AQUA: 1 x 60 µm (2.4 mils) on top of primed concrete
  - Anti-skid openly or fully sprinkled
  - NU-KLAD AQUA: 1 x 60 µm (2.4 mils)
- 

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: base to hardener 70:30; Mixing ratio by weight: base to hardener 75:25 (3:1)

- Material temperature should be between 10°C (50°F) and 30°C (86°F)
  - Mix base and hardener with a mechanical mixer thoroughly until homogeneous
  - Tap water for thinning should be added after mixing the two components
- 

### Induction time

None

---

# NU-KLAD™ AQUA

**Pot life**

3 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

**Anti-skid system**

- Apply NU-KLAD AQUA: 1 x 60 µm (2.4 mils) on top of primed concrete
- Sprinkle anti-skid in the wet layer (open or full)
- Remove excess of anti-skid before overcoating, in case of fully sprinkled
- Apply the second coat of NU-KLAD AQUA: 1 x 60 µm (2.4 mils) by roller on top of the anti-skid

**Airless spray**

**Recommended thinner**

Tap water

**Volume of thinner**

10 - 15% when applied as a primer direct to concrete; 0 - 5% when applied on primed concrete

**Brush/roller**

**Volume of thinner**

10 - 15% when applied as a primer direct to concrete; 0 - 5% when applied on primed concrete

**Cleaning solvent**

Tap water

Notes:

- An adequate cleaning procedure should be used in case of changing from solvent-borne paint to waterborne paints or from waterborne paints to solvent-borne paints
- THINNER 90-53 can be used if necessary

**ADDITIONAL DATA**

Overcoating interval for DFT up to 100 µm (4.0 mils)				
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	12 hours	5 hours	4 hours
	Maximum	21 days	21 days	21 days
polyurethane topcoat	Minimum	48 hours	24 hours	16 hours
	Maximum	5 days	5 days	5 days

Notes:

- Surface should be dry and free from any contamination
- For intervals exceeding the maximum overcoating interval, the surface has to be roughened sufficiently before overcoating



# NU-KLAD™ AQUA

## Curing time for DFT up to 100 μm (4.0 mils)

Substrate temperature	Dry to walk on	Light impact/abrasion	Full cure
10°C (50°F)	12 hours	30 hours	12 days
20°C (68°F)	5 hours	16 hours	7 days
30°C (86°F)	4 hours	10 hours	4 days

Note: Adequate ventilation must be maintained during application and curing

## Pot life (at application viscosity)

Mixed product temperature	Pot life
10°C (50°F)	4 hours
20°C (68°F)	3 hours
30°C (86°F)	2 hours

## SAFETY PRECAUTIONS

- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods

## REFERENCES

- |                                      |                   |      |
|--------------------------------------|-------------------|------|
| • CONVERSION TABLES                  | INFORMATION SHEET | 1410 |
| • EXPLANATION TO PRODUCT DATA SHEETS | INFORMATION SHEET | 1411 |

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

# NU-KLAD™ AQUA

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

