

Description

Centrecoat MMA Asphalt Primer has been developed as a substrate specific primer for Tarmac and Asphalt, being used prior to any suitable Centrecoat MMA product. The product exhibits excellent adhesion to tarmac and asphalt, and the fast curing characteristics allow rapid application of subsequent coatings, mortars or screeds.

Centrecoat MMA Asphalt Primer is supplied as a two pack material, comprising pre-weighed amounts of Base and Catalyst components.

Features

- ▶ Rapid cure, even at low temperatures
- ▶ Very flexible
- ▶ Very good chemical resistance
- ▶ Excellent adhesion
- ▶ Impervious to water
- ▶ Pre-packed units ready for use
- ▶ Easily applied

Preparation

New Tarmac shall be allowed to weather for at least 1 month, or until there is no evidence of residual flux oils. Tarmac and Asphalt surfaces shall be washed with detergent and water and allowed to dry. Extremely smooth Asphalt may require some light texturing by mechanical means.

Mixing

Pour the contents of the Catalyst container into the Base container and thoroughly mix, preferably by mechanical means.

Application

Apply by squeegee to distribute evenly over the floor, and then use a long nap lambswool roller to achieve a nominal application rate of 0.25-0.30kg/m².

Allow to cure for a minimum of 1 hour prior to applying any other suitable Centrecoat MMA product.

Technical Data

- ▶ Viscosity: 300 - 400 cps at 20°C
- ▶ Pot Life: 10 - 15 minutes at 20°C, 20 - 25 minutes at 10°C
- ▶ Colour: Straw coloured liquid
- ▶ Adhesion To Concrete: 3.5MPa (concrete failure)
- ▶ Temperature Range During Application: 5°C - 35°C
- ▶ Temperature Range During Service: -40°C to 60°C
- ▶ Overcoatable: Minimum 60 minutes at 20°C

Coverage Rate

A 5kg pack is sufficient to prime an area of 15-20m². Exceptionally porous surfaces may require a second coat.

Clean Up

Clean equipment with [Centrecoat MMA Tool Cleaner](#) immediately after use.

Storage

Store in dry conditions, out of direct sunlight, at temperatures between 10°C and 20°C. Adequate ventilation of the storage area should be provided. Keep container tightly closed when not in use.

Shelf Life

Centrecoat MMA Asphalt Primer has a minimum shelf life of 12 months when stored in original, unopened containers in accordance with manufacturer's instructions.

Packaging

Available in 5 Kg

Limitations

Do not apply to concrete surfaces. Centrecoat MMA Asphalt Primer will taint food during application, so that all foodstuffs in the immediate vicinity must be removed or properly covered.

Health & Safety

Centrecoat MMA Asphalt Primer is flammable during application, so that adequate safety precautions should be observed. Avoid contact of the material with skin and eyes. Wear gloves and goggles. Wash off splashes immediately with soap and water. Any eye contamination must be rapidly irrigated with copious amounts of clean water, and immediate medical attention sought. Please refer to Material Safety Data Sheet for additional information.

Centrecoat MMA Asphalt Primer shall be applied strictly in accordance with the manufacturer's instructions. For specific advice regarding any aspect of this product, please consult our Technical Department.