

PRODUCT DATA SHEET Centrecoat HB Anti-Corrosive Cladding Paint

Description

Centrecoat HB Anti-Corrosive Cladding Paint is a multi-functional product is designed for application directly onto cladding, and to provide good phosphate-based anti-corrosive protection for iron and steel, whilst being tolerant to application directly onto wood and over suitably prepared old paintwork.

Centrecoat HB Anti-Corrosive Cladding Paint is a low odour, high flashpoint, one-coat primer/finish with high build potential. It has been specially formulated as an emissions-compliant coating and conforms to EU Decopaint Directive 2004/42/CE as a one-pack performance coating (VOC below 500g/l) and Department of Environment PG6/23(04) table 6, having a solvent content of less than 0.6 times the total mass of solids.

Colour & Finish

Available in a wide range of colours including most British Standards, RAL and special colours to customer requirements. Some colours may contain lead-chromate pigments. If lead-free pigmentation is required, please state this when ordering. Semi Matt finish.

Preparation

Apply only to clean, dry and suitably prepared surfaces. On old paintwork, remove all loose and flaky paint back to a firm edge. On all substrates, clean off any oil or greasy residues, dust, scale, rust, etc. The surfaces to be painted should then be lightly flatted, to give a smooth surface with an adequate key, before the application of this product.

Application

Mix thoroughly before use. Centrecoat HB Anti-Corrosive Cladding Paint is designed for application by airless and air-assisted airless spray using a 15-17 thou tip with 50° fan, as well as by conventional spray, brush and roller when thinned appropriately (which will not render the product non-compliant).

Centrecoat HB Anti-Corrosive Cladding Paint can be applied onto previously painted substrates, most types of metal cladding, iron, steel and wood. However, when repainting PVF2 cladding, a surface tolerant primer is required as a first coat to ensure adequate adhesion.

Coating adhesion and performance is in general proportional to the degree of surface preparation. This product is supplied 'ready for use' airless spray application. If required, it should be thinned slightly with Centrecoat HB Anti-Corrosive Cladding Paint Thinner. In hot weather, it may be necessary to add additional solvent to compensate for evaporated solvent. Normal thinning is unlikely to affect the compliant nature of this product.

Do not apply or dry when air or surface temperature is below 5°C, above 30°C or in high humidity or where condensation is likely to occur (i.e. Surface temperature must always be a minimum of 3°C above dew point). Painting should only be carried out under good atmospheric conditions and clement weather. Painting in direct sunlight can

lead to a patchy appearance if the surface temperature is in excess of 30°C.

Preparation, painting and drying should never be undertaken: when the air temperature falls below the minimum temperature for the coating, or during fog, mist, snow, or when rain is imminent, or when the surface to be painted is wet with condensation or when condensation may occur during the drying period.

Overcoating

If a second coat is required, for brush application recoating should ideally be carried out after overnight drying. For spray application anytime after 2 hours or when touch dry. This product may show an adverse reaction if overcoated by certain paints that are based on strong solvents such as xylene.



PRODUCT DATA SHEET Centrecoat HB Anti-Corrosive Cladding Paint

Technical Data

- ▶ Volume Solids: Typically 50%-55%, varying slightly with colour.
- VOC: 390 g/l dependant on colour.
- Flash Point: 32°C
- > Dry Film Thickness: 80 microns in one or two coats. A DFT of 40 microns per coat is recommended for brush
- application and 100 microns for spray application.
- ▶ Wet Film Thickness: 77 microns or 185 microns for spray application.
- Touch Dry: 1.5 hours at 20°C
- Through Dry: 3 hours at 20°C
- Hard Dry: Overnight at 20°C
- Fully Cured: 1 week at 20°C

Coverage

6.9m2 per litre when applied by brush and also 6.9 square metres per litre for spray application. NB. The practical coverage rate depends on many factors and will always be less than the theoretical figure.

Clean Up

Clean all equipment using Centrecoat HB Anti-Corrosive Cladding Paint Thinner immediately. Ensure all lines, tips, etc. are thoroughly flushed out. It is not sufficient to leave equipment filled up with solvent.

Shelf Life

12 months when stored indoors, in original unopened containers, within the temperature range 10°C to 32°C.

Packaging

Available in 5 and 20 Litres.

Limitations

vFamiliarise yourself with MSDS before using this product.