

DAMPShield

103/Q124/Dam

DESCRIPTION:

Coo-Var Dampshield is a two-component resin membrane that is tolerant to residual moisture in concrete floors. This enables earlier access onto the floor than would otherwise be available for the application of screeds, coatings and other floor coverings including carpets, tiles, vinyl and wood. Being solvent free it is low odour during application which allows usage in areas where taint could be a problem.

RECOMMENDED USE:

Coo-Var Dampshield can be used on concrete floors and fine concrete screeds, in the case of unbonded screeds this should not be less than 50mm thick. The surface must be of sufficient quality, continuity and mechanical strength to ensure even coating.

AVAILABILITY:

5 kilo mixed units.

FINISH:

Gloss

COLOUR:

Clear

TYPICAL S.G. (SPECIFIC GRAVITY):

1.05 @ 20 °C

VOLUME SOLIDS:

100%

WET FILM THICKNESS W.F.T

230 microns

DRY FILM THICKNESS D.F.T

230 microns

EXPECTED SPREADING RATE:

20 sq.m / 5 kilo pack
@ recommended D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

N/A

FLASH POINT:

Above 55 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 24 hours @ 20 °C

Hard dry: 72 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

Minimum 12 hours @ 20 °C

APPLICATION SPECIAL CONDITIONS:

See Remarks section

VOC CONTENT:

Max 10 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Roller
(lambswool)

Thinner N/A
(Max vol):

Nozzle size:

Nozzle N/A
pressure:

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: info@coo-var.co.uk

www.coo-var.co.uk

Cleaning solvent: Thinners 16 (Brushwash only)

barrier layer resulting in the pressure / water flow being directed elsewhere.

Recoat interval: Minimum 12 hours @ 20 °C Maximum 48 hours @ 20 °C

HEALTH AND SAFETY:

For hardener see safety data sheet - SDS 11127.
For base see safety data sheet - SDS 11108.

SURFACE PREPARATION:

Concrete surfaces must be prepared by scarifying, vacuum shot-blasting, planing or other suitable method. All traces of concrete hardeners or other contaminants must be removed. The surface must be thoroughly vacuumed to remove concrete dust and then protect against further contamination by suitable means. Surfaces must be free from liquid, water, and the atmosphere must not be condensing.

ISSUED:

24 April 2013

REVISION:

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

MIXING INSTRUCTIONS:

Mix the contents of the hardener component with the base thoroughly using a slow speed power stirrer.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. Do not apply if the temperature is likely to drop below 10 °C during application or during the drying process.

PRECEDING COAT:

N/A

SUBSEQUENT COAT:

Coo-Var Profloor Plus

REMARKS:

The system is selected on the basis of hygrometer readings in accordance with BS 8203. The number of coats to be applied is chosen in accordance with the following table. Relative Coating thickness Humidity Reading %
 75 - 85
 1 coat @ 230 mic 85 - 92 2 coats @
 230 mic / coat 92 - 97 3 coats @
 230 mic / coat
 When laid onto a concrete surface where there is no damp-proof membrane (DPM) or where damage may have rendered the DPM ineffective, due consideration must be given to the possible presence of hydrostatic pressure, and the consequences of creating a

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"