



APPLICATION INSTRUCTIONS - KEIM FIXATIV

KEIM Fixativ is a silicate binding and fixing agent made from pure, liquid potassium silicate for use with KEIM systems. KEIM Fixativ reacts chemically with the surface.

BEFORE PROCEEDING

- Allow a minimum of 15 days for new renders/repairs to dry.
- Lime renders/repairs must be allowed a minimum of 28 days to dry and must have carbonated to a minimum depth of 2.5mm.
- Ensure air and surface temperatures are between 5-30°C.
- Ensure surface moisture content to a depth of 5mm is below 18%.
- Do not apply when there is a likelihood of rainfall within 12 hours.

SURFACE PREPARATION

- Wash all surfaces with clean cold water to remove dust and dirt.

MATERIAL APPLICATION

- Apply a single coat of Keim Fixativ, diluted 50:50 with clean cold water by brush or low pressure spray, ensuring that it is worked well in to the surface.
- Allow to dry for 12 hours before overcoating (if being painted).

For more information visit: www.keim.com/en-gb/literature