



# **PEGAGRAFF® HYDRO**

# Colourless anti-graffiti varnish

- Colourless anti-graffiti protection for porous concrete, natural stone, brick, interior wood, various coatings and paints
- Good UV resistance
- Acid resistant
- Alkali resistant

# **PEGAGRAFF® HYDRO**

#### DESCRIPTION

Pegagraff® Hydro is a clear, satin gloss, two-component waterborne polyurethane acrylic lacquer.

#### RECOMMENDED USE

a) Colourless anti-graffiti protection of many substrates (see list on page 2). b) Colourless varnish giving very good protection for floors, walls and interior surfaces.

#### RECOMMENDED SYSTEM

Painted substrates

In principle, direct application on ALL painted substrates is allowed, with exception of elastomeric coatings, i.e. Murfill. A test surface has to be realised beforehand for heat curing paints and for powder coatings.

Not painted or untreated substrates

Only on reinforced concrete (remaining humidity level < 4 %), Pegagraff Hydro can be applied directly.

Not recommended substrates

a) Do not apply Pegagraff Hydro on a mineral painted substrate where the relative humidity is higher than 6%. This concerns bricks, terra-cotta tiles, renderings, etc. In this case, a white film could be formed and more or less important adhesion loss will appear.

b) Do not apply Pegagraff Hydro directly on not painted metal substrates such as aluminium, steel, zinc, stainless steel, cupper,etc.

c) Do not apply Pegagraff Hydro directly on bare wood for exterior applications.

d) Do not apply Pegagraff Hydro directly on rough surfaces such as plaster, rough brickwork (masonry), etc.

#### **TECHNICAL DATA**

Density (g/cm $^3$ ):  $\pm 1,04$  Gloss Level: Satin

Gloss level at 60°: Satin gloss: 35%
Solids Content in weight: ± 42 % (Mischung)
Solids content in volume: ± 40 % (Mischung)

# DRY TIMES BY 20° C/RV 50%

Touch dry: 2 hours
Dry to handle: 4 hours
Dry to recoat: 5 hours

Pot Life: 10°C: 2,5 hours / 20°C: 2 hours / 30°C: 1 hour

# RECOMMENDED WET FILM THICKNESS

125 µm

## RECOMMENDED DRY FILM THICKNESS

50 µm

## THEORETICAL CONSUMPTION

5 - 8 m<sup>2</sup>/l

# PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

#### SURFACE PREPARATION

Apply on a dry, clean and degreased substrate. Glossy and satin surfaces should be roughened up previously. When applying Pegagraff Hydro on Murfill, this should first be insulated with a coat of Paracem. When repainting surfaces protected with Pegagraff Hydro, first an adhesion primer in Pegalink has to be applied.

Not painted metal substrates such as steel, aluminium, stainless steel, cupper etc. have to be

treated with a suitable paint before applying Pegagraff Hydro.

#### **DIRECTIONS FOR USE**

Add the component B (small packing) completely and progressively to component A (large packing) with an electric stirrer. Allow the mixture to rest for about 5 minutes (defoaming). Although the mixture does not show a clearly perceptible thickening after 2 hours, we advise not to use the mixture anymore because of a diminished solvent resistance and reduced flow.

#### APPLICATION CONDITIONS

> 5°C < 80% B.H.

Apply in a well-ventilated place.

#### **APPLICATION & THINNING: BRUSH**

All types can be used. Do not dilute.

#### **APPLICATION & THINNING: ROLLER**

Preferably apply with a short haired roller. Do not diluted.

# **APPLICATION & THINNING: AIRLESS SPRAY**

Nozzle: 09 - 013 / Pressure: 120 - 180 bars. Do not dilute.

#### **APPLICATION & THINNING: AIR-ATOMISED SPRAY**

Do not dilute.

#### **CLEANING OF EQUIPMENT / SPILLS**

Water.

#### **REMARKS**

With a consumption less than 5  $\,\mathrm{m^2/l}$ , or applied too thick, Pegagraff Hydro can fade; please respect the consumption values.

#### **SAFETY DATA**

 VOC level:
 20 g/l

 VOC readymix:
 20 g/l

 VOC category:
 A/j

 VOC limit:
 140 g/l

Remarks regarding safety: Consult Safety Data Sheet and Safety Information

printed on the can.

## **SHELF LIFE**

At least 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Date issued:** 13/04/2021

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V. Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T : +31 (0) 165 593 636 F : +31 (0) 165 593 600 info@rust-oleum.eu Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
Index Description (1) 147
In

Rust-Oleum France S.A.S. 38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@nust-aleum eu