

RUST-OLEUM®
— INDUSTRIAL —



METAL CLADDING TOPCOAT

Water-based satin gloss decorative topcoat

- Improves life expectancy of metal cladding
- Easy to clean and maintain
- Excellent flow and aspect with brush, roller or spray
- High filling and hiding power
- Tintable in almost any colour

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

METAL CLADDING TOPCOAT

DESCRIPTION

Waterborne satin gloss decorative topcoat for use on metal objects and cladding.

RECOMMENDED USE

Finish on metal cladding or any metal surface primed with Metal Cladding Primer, PVDF Primer, NOXYDE® or PEGANOX®. Also directly onto aged Plastisol in good condition.

TECHNICAL DATA

Density (g/cm³):	1,3
Gloss Level:	Satin
Corrosion Class:	C1/C2 low protection
Solids content in volume:	33%

DRY TIMES BY 20° C/RV 50%

Touch dry:	1 hour
Dry to handle:	5 hours
Dry to recoat:	8 hours
Fully cured:	2 days

RECOMMENDED WET FILM THICKNESS

130 µm

RECOMMENDED DRY FILM THICKNESS

45 µm

THEORETICAL CONSUMPTION

8 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Can be applied directly on substrates primed with Metal Cladding Primer, NOXYDE® or PEGANOX®. Can also be applied on old sound paints; glossy paints will be roughed up slightly. In all cases, the substrate must be sufficiently dry and clean. Apply 1 - 2 coats of the Metal Cladding Topcoat.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Temperature minimum 10°C / max. 80% R.H.

APPLICATION & THINNING: BRUSH

Apply undiluted in 2 coats by preference.

APPLICATION & THINNING: ROLLER

Apply undiluted in 2 coats by preference. Use short nap roller.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 013 – 015 / Pressure: 160 bar. 1 coat is sufficient in most cases, if there is no big colour difference with the previous coat. If necessary dilute with water.

Check WFT and avoid over thicknesses, especially for dark colors.

Too high film thickness can result in blistering.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended.

CLEANING OF EQUIPMENT / SPILLS

Water

REMARKS

Do not apply in full sun or too hot conditions, to avoid a decreased flow.

The product can remain a little sticky if it is used on new Plastisol cladding.

SAFETY DATA

VOC level:	128 g/l
VOC readymix:	128 g/l
VOC category:	A/d
VOC limit:	130 g/l
Remarks regarding safety:	Consult Material Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 24/06/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu