

RUST-OLEUM®
— INDUSTRIAL —



ASPHALT RESTORER



Freshes up discoloured asphalt

- Upgrades drab, grey, stained asphalt and tarmac
- Provides an 'as new' appearance
- Covers old line markings and repairs
- Avoids disruptive and costly re-surfacing

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

ASPHALT RESTORER

DESCRIPTION

A one component high quality bitumen based coating with fillers and special flow additives. For refurbishing car parks, driveways and footpaths.

RECOMMENDED USE

For refurbishing car parks, driveways and footpaths.

DRY TIMES BY 20° C/RV 50%

Touch dry:	30 minutes
Dry to recoat:	2 - 5 hours
Fully cured:	2 - 5 hours. Rain will delay curing by trapping solvents within the coating.

THEORETICAL CONSUMPTION

5 - 10 m² per 5 litres, depending on the surface.

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

SURFACE PREPARATION

Surfaces should be dry and free of any loose material. Moss etc. should be removed by scraping and/or jet washing and the surface left to dry thoroughly.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Do not apply during rainfall. Protect from rain for at least 30 minutes after application.

APPLICATION & THINNING: BRUSH

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

APPLICATION & THINNING: ROLLER

The product should be applied generously but evenly in one coat using a roller or brush. Small pits and fissures can be filled with a stiff mortar consisting of dry sand mixed with the product. Pits and fissures should be primed with the product 5478 before trowelling in the mortar.

REMARKS

This product is intended as a surface coating. It is not designed to strengthen or repair weak or damaged surfaces. This product is designed for use on bitumen based surfaces. It could soften surfaces which contain coal tar. If in doubt, apply a test area and check after 24 hours that no softening has occurred.

SAFETY DATA

VOC level:	286 g/l
VOC ready mix:	286 g/l
VOC category:	A/i
VOC limit:	500 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 25°C.

Date issued: 24/06/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu