

**RUST-OLEUM®**  
— INDUSTRIAL —



## **SURFA-ETCH® 108**

# **Etching solution for floors and metal**

- Improves the adhesion of coating systems
- Neutralizes alkaline salts
- Also ideal to remove 'white rust' from metal
- No objectionable odour or fumes
- Non-flammable

**KNOW-HOW TO PROTECT™**

**WWW.RUST-OLEUM.EU**

# SURFA-ETCH® 108

## DESCRIPTION

Etching solution for etching smooth concrete surfaces, masonry, galvanized steel and aluminum before applying a coating system.

## RECOMMENDED USE

Surfa-Etch 108 Etching Solution should be used for etching smooth concrete surfaces, masonry, galvanised steel and aluminium before applying a RUST-OLEUM coating system. Surfa-Etch 108 neutralizes alkaline contaminations and removes zinc- and aluminium corrosion products ("white rust") Surfa-Etch 108 should be applied with a stiff nylon brush or a broom.

## THEORETICAL CONSUMPTION

6 - 8 m<sup>2</sup>/l

## PRACTICAL CONSUMPTION

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

## DIRECTIONS FOR USE

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt and all other surface contaminations as much as possible. Degrease by means of alkaline cleaning, high pressure (steam) cleaning or, for small patches, by volatile solvent cleaning. Apply Surfa-Etch 108 Etching Solution liberally and scrub it into the surface. Allow to stand for 10-15 minutes, depending on temperature, and clean thoroughly by flushing with plenty of fresh water. Do not allow the Surfa-Etch 108 Etching Solution to dry before rinsing! Concrete and masonry may need a second treatment. After cleaning, remove any remaining water and allow to dry completely, as moisture left on the surface or entrapped into pores may cause failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

## APPLICATION CONDITIONS

Temperature of air, substrate and material between 5 and 35°C.

## SAFETY DATA

VOC level: 45 g/l  
Remarks regarding safety: Consult Safety Data Sheet and Safety Information printed on the can.

## PH

1.0000

## SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 24/06/2022

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)