

Hempaxane Light

Product characteristics

Description

Hempaxane Light 55030 is a two-component, high-solids, glossy, polysiloxane enamel with excellent gloss and colour retention.

Recommended use

As an isocyanate free glossy decorative and protective finishing coat for structures in severely corrosive atmospheric environment.

Service temperature:

- Maximum, dry exposure only: 120°C [248°F].

Product safety

Flash point 33°C [91°F]

VOC content mixed product

Legislation	Value
EU	203 g/L [1.69 lb/US gal]
US (coatings)	201 g/L [1.68 lb/US gal]
US (regulatory)	201 g/L [1.68 lb/US gal]
China	203 g/L [1.69 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website. VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code

55030

Product components

Base 55039

Curing Agent 98000

Standard shade* / code

Light grey 17380 **

Gloss

Glossy

Volume solids

83 ± 2%

Specific gravity

1.4 kg/L [12 lb/US gal]

Reference dry film thickness

75 micron [3.0 mils]

Surface preparation

Cleanliness

- According to Hempel's Specification.

New build:

- According to Hempel's Specification.

Maintenance and Repair

- According to Hempel's Specification.

Consult Hempel's separate Surface Preparation Guidelines for more details.

* Wide range of colours is available via Hempel's Multi-Tint® system.

** Colour stability may be affected by exposure to harsh chemical and/or high temperatures.

Hempaxane Light

Application

Mixing ratio

Base 55039 : Curing Agent 98000
 (56 : 44 by volume)

Stir well before use.

Thinner

Hempel's Thinner 08080

Cleaner

Hempel's Tool Cleaner 99610

Pot life

Product temperature	20°C [68°F]
Pot life	4 hours

Application method

Tool	Thinning max vol.	Application parameters
Airless spray	10%	Nozzle pressure: 100-125 bar [1500 psi] Nozzle orifice: 0.017-0.021"
Brush	5%	Not Applicable.

Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

Film thickness

Specification range	Low	High	Recommended
Dry film thickness	50 micron [2.0 mils]	100 micron [3.9 mils]	75 micron [3.0 mils]
Wet film thickness	60 micron [2.5 mils]	120 micron [5 mils]	90 micron [3.5 mils]
Theoretical spreading rate	17 m²/L [690 sq ft/US gal]	8.3 m²/L [340 sq ft/US gal]	11 m²/L [450 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness.

Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Surface temperature must be above 0°C [32°F] during application and curing.

Relative Humidity:

- Relative humidity must be above 30% during curing.

Application remarks

- Two coats of the topcoat may be necessary to obtain full hiding power.

Drying and overcoating

Product compatibility

- Previous coat: None or according to Hempel's specification. Recommended products are: Hempel's Galvosil, Hempadur
- Subsequent coat: None.

Drying time

Surface temperature	20°C [68°F]
Touch dry	hours 2½
Hard dry	hours 5½

Determined for dry film thickness 75 micron [3.0 mils] at standard conditions, see Hempel's Explanatory Notes for details.

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- Condensation on the freshly applied coating should be avoided.

Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be clean before overcoating.

Other remarks

- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

Hempaxane Light

Storage

Shelf life

Ambient temperature	25°C [77°F]	35°C [95°F]
Base	24 months	16 months
Curing Agent	18 months	12 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

Storage conditions

- The curing agent is sensitive to moisture. Store in a dry place and keep the can tightly closed until use.

Additional documents

Additional information is available at the Hempel website [hempel.com](https://www.hempel.com) or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.