



OWAYELL*

GELCOAT AND METAL RENOVATOR

Product description	OWAYELL removes yellow staining, limescale and rust spots from gelcoat, stainless steel etc. in minutes.
Properties	• Removes yellow staining, mould, black stain and rust. • Brightens and whitens gelcoats. • Dissolves limescale, sea salt and water marks. • Cleans and renews anti-slip surfaces. • Disintegrates dirt caused by micro-organisms and barnacle/shell residue. • Removes streaks and rust traces. Passivates steel. • Restores shine to stainless steel (removes rust spots), anodised aluminium and chromes surfaces. • Easy to use and fast acting.
Basic uses	• Polyester/Gelcoat, Anodised Aluminium, Plexiglass, Glass, Stainless Steel... • Hull, Keel, Propeller Shaft... • Decks, Portholes, Pulpits, Stanchions, Cleats, Chocks, Rigging... • Masts, Spars...
Technical data	Composition: Acid base. pH: 1. Specific Gravity (at 20°C): 1.092 ± 0.05. Flash point: > 61°C. VOC: Outside the scope of EC Directive 2004/42.
Application tools	Brush, Roller, Cloth.
Good application practice	Protect surfaces you do not wish to treat. Do not apply to surfaces in direct sunlight during the hottest hours of the day. Limit contact time to 5 minutes when applying to paint, varnish, lacquer or non-rusted steel. Always test on a small inconspicuous area first. Use appropriate protective clothing - Gloves, Goggles...
Application	Shake well before use. Do not dilute. Apply OWAYELL to the surface to be treated Allow to work 5 to 10 minutes (20°C @ 50% RH). No need to scrub surface. Rinse with plenty of fresh clean water, working from top to bottom. If required repeat process. TIP: For surfaces heavily encrusted with limescale brush surface with nylon brush 10 minutes after applying first application. DO NOT rinse. Apply 2nd application and leave to work 5 to 10 minutes. Rinse with plenty of fresh clean water. ADDITIONAL USES Liquid sander to passivate raw steel and aluminium before painting. Dilute 1 part OWAYELL to 5 parts water. Apply to surface and leave to work 10 minutes. Rinse off. Dry and immediately apply finish.

The information set out cons are purely illustrative and are not the responsibility of the manufacturer, the application of products not made under his supervision.

* Dangerous, respect the use precaution.

Restrictions	Do not use on galvanised metal or raw aluminium.
Clean up	Water.
Storage	Store left over product in original container Keep from freezing and high temperatures.
General information	Every care is taken to ensure that the information provided in this technical data sheet is accurate. OWATROL International is unable to guarantee results as we have no control over the conditions under which our products are applied. For further advice and information please contact our technical department by email at info@owatrol.com or the local OWATROL Agent for your country. The information above is correct at the date of issue. All other OWATROL products named in this document should be used as per label instructions and the technical data sheet.
Safety	Refer to the safety data sheet (MSDS) available at www.owatrol.com and text on the packaging. Keep out of the reach of children.
Issue date	March 2016.

* Same manufacturer



The information set out consists of purely illustrative and are not the responsibility of the manufacturer, the application of products not made under his supervision.

04/16 - RCS Tours 331 998 484 - Photo: Strezhev Pavel