

Hempadur 47960

Product characteristics

Description

Hempadur 47960 is a two-component polyamide adducts cured, high build epoxy paint which combines a relatively high volume solids content with a short drying time. VOC compliant. Prolonged recoating properties. Pigmented with zinc phosphate.

Recommended use

As a primer in mild to medium atmospheric environments.
As an intermediate or finishing coat in epoxy systems in medium to severely corrosive atmospheric environment.
As a one coat self priming epoxy topcoat available in various shades.
May be used directly on cured zinc silicate (GALVOSIL products) or spray-metallised surfaces to minimise popping.

Service temperature:

- Maximum, dry exposure only: 140°C [284°F].

Product safety

Flash point 24°C [75°F]

VOC content mixed product

Legislation	Value
EU	246 g/L [2.05 lb/US gal]
US (coatings)	246 g/L [2.05 lb/US gal]
US (regulatory)	246 g/L [2.05 lb/US gal]
China	246 g/L [2.05 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website. VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code

47960

Product components

Base 47969
Curing Agent 98140

Standard shade / code

Grey 11480 *

Gloss

Semi-gloss

Volume solids

72 ± 2%

Specific gravity

1 kg/L [8 lb/US gal]

Reference dry film thickness

100 micron [3.9 mils]

Surface preparation

Cleanliness

- Remove oil, grease and other contaminants by suitable detergent cleaning.
- Remove salts, detergents and other contaminants by high pressure fresh water cleaning.

New build:

- Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SP 10 (SSPC).
- Remove dust, blast media and loose materials.

Maintenance and Repair

- Spot abrasive blasting to min. PSa 2½ (ISO 8501-2) / SP 10 (SSPC).
- Remove dust, blast media and loose materials.

Consult Hempel's separate Surface Preparation Guidelines for more details.

Hempadur 47960

Application

Mixing ratio

Base 47969 : Curing Agent 98140
(5 : 1 by volume)

Stir well before use.

Thinner

Hempel's Thinner 08450

Cleaner

Hempel's Tool Cleaner 99610

Pot life

Product temperature	20°C [68°F]
---------------------	----------------

Pot life	60 min
----------	--------

Application method

Tool	Thinning max vol.	Application parameters
Airless spray	5%	Nozzle pressure: 225 bar [3300 psi] Nozzle orifice: 0.019-0.021"
Brush	5%	Not Applicable.

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

Film thickness

Specification range	Low	High	Recommended
Dry film thickness	80 micron [3.1 mils]	150 micron [5.9 mils]	100 micron [3.9 mils]
Wet film thickness	110 micron [4 mils]	210 micron [8 mils]	130 micron [5 mils]
Theoretical spreading rate	9 m²/L [370 sq ft/US gal]	4.8 m²/L [200 sq ft/US gal]	7.2 m²/L [290 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness.

Application conditions

- Surface temperature must be above 0°C [32°F] during application and curing.
- Temperature of product must be above 15°C [59°F] during application.
- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

Drying and overcoating

Product compatibility

- Previous coat: According to Hempel's Specification. Recommended products are: Hempadur Zinc 17360, Hempel's Galvosil 15700, Hempel's Galvosil 15780
- Subsequent coat: None or according to Hempel's specification. Recommended products are: Hempathane, Hempaxane

Drying time

Surface temperature		20°C [68°F]
Touch dry	min	60
Hard dry	hours	3

Determined for dry film thickness 100 micron [3.9 mils] at standard conditions, see Hempel's Explanatory Notes for details.

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be dry and clean prior to application.

Other remarks

- Epoxy coats have an inherent tendency of chalking in outdoor exposure. This does not affect the performance of the coating.
- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

Hempadur 47960

Storage

Shelf life

Ambient temperature	25°C [77°F]	35°C [95°F]
Base	36 months	24 months
Curing Agent	36 months	24 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

Additional documents

Additional information is available at the Hempel website [hempel.com](https://www.hempel.com) or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.