

## Acrylic Intumescent

**PRODUCT DESCRIPTION** A single component, solvent borne, borate free, high solids, low VOC intumescent coating designed to provide fire protection to structural steelwork.

Independently tested at accredited laboratories to BS476 Parts 20-21, AS 1530.4-2005 and AS 4100, and third party assessed and certified.

**INTENDED USES** To provide up to 60 minutes fire protection on 'I' sections beams, columns and hollow sections.

Suitable for both off-site and on-site application due to its ease of use, fast drying and handling properties. Can be used over a wide range of approved priming systems.

A version with greater water resistance is available which allows for Interchar 2060 to remain untopcoated for up to 6 months exterior exposure provided there is no pooled/heavy running water, or frequent high humidity conditions.

### PRACTICAL INFORMATION FOR INTERCHAR 2060

<b>Colour</b>	White (HFA060), White C (HFA062)			
<b>Gloss Level</b>	Matt			
<b>Volume Solids</b>	75% ± 2% (measured according to ISO 3233 and ICF Method)			
<b>Typical Thickness</b>	350-750 microns (14-30 mils) dry equivalent to 467-1000 microns (18.7-40 mils) wet per coat			
<b>Theoretical Coverage</b>	1 m <sup>2</sup> /litre at 750 microns d.f.t and stated volume solids 40 sq.ft/US gallon at 30 mils d.f.t and stated volume solids			
<b>Practical Coverage</b>	Allow appropriate loss factors			
<b>Method of Application</b>	Airless Spray, Brush			
<b>Drying Time</b>	Overcoating interval with self			
<b>Temperature</b>	<b>Touch Dry</b>	<b>Hard Dry</b>	<b>Minimum</b>	<b>Maximum</b>
10°C (50°F)	45 minutes	22 hours	8 hours <sup>2</sup>	Extended <sup>1</sup>
15°C (59°F)	40 minutes	18 hours	6 hours <sup>2</sup>	Extended <sup>1</sup>
25°C (77°F)	20 minutes	16 hours	4 hours <sup>2</sup>	Extended <sup>1</sup>

<sup>1</sup> See International Protective Coatings Definitions and Abbreviations

<sup>2</sup> Sealer coat should be applied as soon as possible after completion of the final coat of Interchar 2060 (minimum 2-4 hours for Intersheen 579; 24 hours for other topcoats). However, d.f.t. must be checked to ensure that specified thickness has been achieved before any sealer coat is applied.

All drying time data has been quoted at the typical thickness of 750 microns (30 mils) d.f.t.

For application at ambient temperatures of 25°C (77°F) and above, a tropical grade is available. See Product Characteristics.

### REGULATORY DATA

<b>Flash Point (Typical)</b>	5°C (41°F)	
<b>Product Weight</b>	1.37 kg/l (11.4 lb/gal)	
<b>VOC</b>	230 g/kg	EU Solvent Emissions Directive (Council Directive 2010/75/EU)
	290g/l	EU Product Directive (Council Directive 2004/42/CE)

## Acrylic Intumescent

### SURFACE PREPARATION

All surfaces to be coated should be clean and free from contamination. Prior to application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

### Primed Surfaces

Interchar 2060 should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be of normal appearance, dry and free from all contamination, and Interchar 2060 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC SP6, Abrasive Blasting, or SSPC SP11, Power Tool Cleaning) and patch primed prior to the application of Interchar 2060.

### Metallic Zinc Primed Surfaces

Interchar 2060 can be applied over approved epoxy metallic zinc primers. Ensure that the primed surface is clean, dry and free from contamination and zinc salts, prior to application of the Interchar 2060. Ensure zinc primers are fully cured before overcoating. The use of a tie coat, typically Intergard 269 or Intergard 276, is recommended to prevent accumulation of zinc salts.

### APPLICATION

<b>Mixing</b>	This material is a one component coating and should always be mixed thoroughly with a power agitator before application.	
<b>Mix Ratio</b>	Not applicable	
<b>Airless Spray</b>	Recommended	Tip Range 0.48-0.59 mm (19-23 thou) Total output fluid pressure at spray tip not less than 176 kg/cm <sup>2</sup> (2503 p.s.i.)
<b>Air Spray (Pressure Pot)</b>	Not recommended	
<b>Brush</b>	Suitable	Recommended for small areas and repairs, multiple coats will be necessary to achieve the required dry film thickness.
<b>Roller</b>	Not recommended	
<b>Thinner</b>	Not normally required	
<b>Cleaner</b>	International GTA007	
<b>Work Stoppages</b>	Thoroughly flush all equipment with International GTA007. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage.	
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA007. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.	
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

## Acrylic Intumescent

### PRODUCT CHARACTERISTICS

The detailed Interchar 2060 Application Guidelines should be consulted prior to use.

Required film build in one coat is best attained by airless spray. When applying by methods other than airless spray, the required film build is unlikely to be achieved.

Low or high temperatures may require specific application techniques to achieve maximum film build. Over-application of Interchar 2060 will extend both the minimum overcoating periods and handling times.

For optimum drying properties when applying Interchar 2060 at dry film thicknesses above 750µm (30 mils), it is recommended that two coats are applied, observing the minimum overcoating times between coats. It is possible to apply Interchar 2060 up to 1500microns (80 mils) dry film thickness in a single coat, however, drying, hardness development and handling times will be longer.

When applying Interchar 2060 by brush, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

For optimum application and drying characteristics, the air and substrate temperature should be greater than 5°C (41°F) and relative humidity less than 85%. Surface temperature must always be a minimum of 3°C (5°F) above dew point.

When applying Interchar 2060 in confined spaces ensure adequate ventilation.

The finished appearance of Interchar 2060 is dependent on application method. For visible areas spray application is preferred. High decorative finishes may require additional preparation before application of sealer coat. The final surface finish is dependent on application method. Avoid using a mixture of application methods whenever possible.

A version with greater water resistance characteristics, Interchar 2060 White C, is available, which may remain untopcoated for up to 6 months exterior exposure. However, Interchar 2060 (whether topcoated or not) should be protected from ponding/pooling or running water. Interchar 2060 is not designed for frequent water immersion/soaking.

### Tropical Grade

For improved product workability in warmer climates, a tropical grade version is available (White HFA061, White C HFA063). Interchar 2060 Tropical Grade has the following characteristics. Volume Solids 75% ±2% ; VOC 300g/l, Flash Point 27°C (81°F).

### Drying Times:

<u>Temperature</u>	<u>Touch Dry</u>	<u>Hard Dry</u>	<u>Overcoating Interval with Self</u>	
			<u>Minimum</u>	<u>Maximum</u>
25°C (77°F)	60 minutes	24 hours	8 hours <sup>2</sup>	Extended <sup>1</sup>
40°C (104°F)	30 minutes	18 hours	6 hours <sup>2</sup>	Extended <sup>1</sup>

<sup>1</sup> See International Protective Coatings Definitions and Abbreviations.

<sup>2</sup> Sealer coat should be applied as soon as possible after completion of the final coat of Interchar 2060 (minimum 2-4 hours for Intersheen 54 and 579; 24 hours for other topcoats). However, d.f.t. must be checked to ensure that specified thickness has been achieved before any sealer coat is applied.

### SYSTEMS COMPATIBILITY

Interchar 2060 has been tested as part of a coating system for use in fire situations over a wide range of approved priming systems. The following primers are approved for use with Interchar 2060

Intercure 200	Intercure 200HS
Intergard 251	Intergard 269
Interprime 306	Interseal 670HS
Interseal 1052	Interzinc 42
Interzinc 52	

The following topcoats are approved for use with Interchar 2060

Intercryl 525	Interfine 878	Intersheen 54
Intersheen 579	Interthane 870	Interthane 990
Interthane 990SG		

Where a polysiloxane topcoat is envisaged, application of a tie coat over Interchar 2060 will be necessary; please consult the Application Guidelines for further information.

Note : In environmental exposure conditions other than internal, dry as per ISO 12944 Part 2, C1 classification, Interchar 2060 must always be suitably topcoated. Consult International Protective Coatings for more details

## Acrylic Intumescent

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Interchar Application Guidelines

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Vol	Pack
	20 litre	20 litre	20 litre
For availability of other pack sizes, contact International Protective Coatings.			

SHIPPING WEIGHT (TYPICAL)	Unit Size	
	20 litre	29.2 kg

STORAGE	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.
---------	------------	--

### Important Note

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 09/03/2020.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

**[www.international-pc.com](http://www.international-pc.com)**