

PRODUCT DESCRIPTION

A low VOC, high performance, two component, isocyanate free crosslinking acrylic finish which provides good durability in terms of colour and gloss retention.

INTENDED USES

Designed as a finish coat for use in both new construction and industrial maintenance. For use in a wide variety of aggressive environments including offshore structures, petrochemical facilities, bridges, pulp and paper mills, and power plants.

Suitable for both site and factory application situations and is ideal where legislation prevents the use of isocyanates and restricts solvent levels.

PRACTICAL INFORMATION FOR INTERFINE 629HS

Colour	Wide range via the Chromascan system			
Gloss Level	High Gloss			
Volume Solids	65% ± 3% (depends on colour)			
Typical Thickness	50 microns (2 mils) dry equivalent to 77 microns (3.1 mils) wet			
Theoretical Coverage	13 m ² /litre at 50 microns d.f.t and stated volume solids 521 sq.ft/US gallon at 2 mils d.f.t and stated volume solids			
Practical Coverage	Allow appropriate loss factors			
Method of Application	Airless Spray, Air Spray, Brush, Roller			
Drying Time	Overcoating interval with self			
Temperature	Touch Dry	Hard Dry	<i>Minimum</i>	<i>Maximum</i>
10°C (50°F)	2 hours	30 hours	30 hours	Extended ¹
15°C (59°F)	90 minutes	24 hours	24 hours	Extended ¹
25°C (77°F)	60 minutes	18 hours	18 hours	Extended ¹
40°C (104°F)	45 minutes	6 hours	6 hours	Extended ¹

¹ See International Protective Coatings Definitions and Abbreviations

REGULATORY DATA

Flash Point	Part A 32°C (90°F); Part B 40°C (104°F); Mixed 40°C (104°F)		
Product Weight	1.55 kg/l (12.9 lb/gal)		
VOC	2.80 lb/gal (336 g/l) 212 g/kg	EPA Method 24 EU Solvent Emissions Directive (Council Directive 1999/13/EC)	
See Product Characteristics section for further details			

**SURFACE
PREPARATION**

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Primed Surfaces

Interfine 629HS should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination and Interfine 629HS must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC-SP6, Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning) and patch primed prior to the application of Interfine 629HS.

APPLICATION

Mixing	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.			
Mix Ratio	7 part(s) : 1 part(s) by volume			
Working Pot Life	10°C (50°F) 10 hours	15°C (59°F) 5 hours	25°C (77°F) 2 hours	40°C (104°F) 1 hour
Airless Spray	Recommended	Tip Range 0.32-0.48 mm (13-19 thou) Total output fluid pressure at spray tip not less than 155 kg/cm² (2204 p.s.i.)		
Air Spray (Pressure Pot)	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E	
Air Spray (Conventional)	Suitable	Use suitable proprietary equipment		
Brush	Suitable	Typically 40-50 microns (1.6-2.0 mils) can be achieved		
Roller	Suitable	Typically 40-50 microns (1.6-2.0 mils) can be achieved		
Thinner	International GTA220 (or International GTA415)	Do not thin more than allowed by local environmental legislation		
Cleaner	International GTA822 or International GTA415			
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

**PRODUCT
CHARACTERISTICS**

Level of sheen and surface finish are dependent on application method. Avoid using a mixture of application methods whenever possible. Best results will be obtained by a consistent application method. Best results in terms of gloss and appearance will always be obtained by conventional air spray application.

For brush and roller application, and in some colours, two coats of Interfine 629HS may be required to give uniform coverage. This is particularly true for bright colours such as oranges or yellows when using organic pigments. Best practice is to use a colour compatible intermediate or anti-corrosive coating under the Interfine 629HS.

When overcoating after weathering or ageing, ensure the coating is fully cleaned to remove all surface contamination such as oil, grease, salt crystals and traffic fumes, before application of a further coat of Interfine 629HS.

This product will not cure adequately below 5°C (41°F). For maximum performance ambient curing temperatures should be above 10°C (50°F).

Condensation occurring during or immediately after application may result in a matt finish and an inferior film.

Premature exposure to ponding water will cause colour change, especially in dark colours and at low temperatures.

When applying Interfine 629HS in confined spaces ensure adequate ventilation.

This product is not recommended for use in immersion conditions. When severe chemical or solvent splashing is likely to occur contact International Protective Coatings for information regarding suitability.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

**SYSTEMS
COMPATIBILITY**

The following primers/intermediates are recommended for Interfine 629HS:

Intercure 200	Interplus 356
Intercure 420	Interseal 670HS
Intergard 251	Interzinc 52
Intergard 269	Interzone 505
Intergard 475HS	Interzone 1000
Interplus 256	Interzone 954

Interfine 629HS is designed only to be topcoated with itself.

For further information on alternative primers/intermediates, consult International Protective Coatings.

**ADDITIONAL
INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

**SAFETY
PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 litre	17.5 litre	20 litre	2.5 litre	2.5 litre
	5 US gal	4.36 US gal	5 US gal	0.63 US gal	1 US gal
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT	Unit Size	Part A		Part B	
	20 litre	30.1 kg		3 kg	
	5 US gal	62.2 lb		6.4 lb	
STORAGE	Shelf Life	18 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Issue date: 01/12/2011

Copyright © AkzoNobel, 01/12/2011.

 , International and all product names mentioned in this publication are trademarks of, or licensed to, AkzoNobel.

www.international-pc.com