

# MAPECOAT I 24

Two-component epoxy paint for anti-acid coatings on concrete surfaces.



## WHERE TO USE

Protection of floors, reservoirs and concrete pipes in contact with aggressive chemical agents such as acids, alkalis and hydrocarbons.

### Some application examples

- Chemical protection of sewage pipes.
- Protective coating of purification tanks.
- Chemical and mechanical protection of industrial floorings.
- Protecting recovery tanks for oil, hydrocarbons, first-flush rainwater, etc.

## TECHNICAL CHARACTERISTICS

**Mapecoat I 24** is a two-component epoxy-resin based paint with special pigments that provide excellent covering capability, prepared according to a formula developed in the MAPEI Research Laboratories.

After drying completely, **Mapecoat I 24** resists the aggressive action of acids, alkalis, salts, oils, hydrocarbons and solvents, as shown in Table 1 overleaf. **Mapecoat I 24** resists frost, maintaining the appearance of the surface treated.

## RECOMMENDATIONS

- Do not use **Mapecoat I 24** on damp surfaces if **Triblock P** has not previously been applied.
- Do not dilute **Mapecoat I 24** with solvents or water.
- Do not apply **Mapecoat I 24** if rain is imminent.
- Do not apply **Mapecoat I 24** at temperatures below +5°C.
- Do not apply **Mapecoat I 24** on hot surfaces or surfaces exposed to direct sunlight.
- During hot weather, before mixing the two parts, avoid their exposure to direct sun. It is recommended to store them for at least 24 hours at +10°C.
- Do not apply **Mapecoat I 24** on dusty or crumbly surfaces.
- Do not apply **Mapecoat I 24** on surfaces subject to rising damp (consult our Technical Services Department).
- Do not add **Mapecolor Paste** if the product is supplied ready-coloured.

## APPLICATION PROCEDURE

### Preparation of the substrate

The surfaces to be coated must be completely clean, solid and dry.

Sandblast surfaces to remove loose particles, dust, grease, and traces of form-release oils and paint.

Seal cracks or deteriorated areas with products from the **MapegROUT** range.

Seal all pores and gravel clusters and level off any uneven areas in the sub-layer with **Mapectin** fine-textured smoothing and levelling compound.

Porosities and small surface imperfections can be levelled with **Mapectin** smoothing compound.

In case of damp substrates **Mapecoat I 24** must be used after applying **Triblock P**, three-component epoxy-cementitious primer (consult the technical data sheet for **Triblock P**).

**Triblock P**, diluted with water, can be used as it is, or with sand, such as **Quartz 0.25** or **Quartz 0.5**, which should be added when a skim coat suitable on irregular concrete surfaces is desired.

**Mapecoat I 24** can only be applied when the complete curing of the substrate has occurred.

### Preparing the paint

The two components which make up **Mapecoat I 24** must be mixed together.

Pour component B (hardener) into component A (resin) and mix with a stirrer at low speed to avoid the formation of air bubbles, until a homogeneous paste is obtained. Do not use partial quantities of the components, thus avoiding accidental errors in dosage that would compromise the hardening of **Mapecoat I 24**.

**Mapecoat I 24** is available in 12 standard colours, other RAL colours are available on request. Please contact Technical services for further details.

### Applying the paint

**Mapecoat I 24** can be applied with traditional methods, that is with brush, roller, or airless spray gun in at least 2 coats. The second coat can be applied from 6 to 24 hours later, depending on ambient conditions. Protect the coated surface from rain for at least 12 hours.

**Mapecoat I 24** is ready for light foot traffic after 24 hours.

### Maintenance during application

The surface coated with **Mapecoat I 24** can be washed with water and detergents (after a preliminary test, given the large number of cleaning products on the market).

Once hardened the product may only be removed mechanically.

### Cleaning

Brushes, rollers and airless spray guns can be cleaned with ethyl alcohol before **Mapecoat I 24** dries. Once hardened the product may only be removed mechanically.

## CONSUMPTION

400-600 g/m<sup>2</sup> per coat.

## PACKAGING

**Mapecoat I 24** is available in 5 kg units (component A: 4 kg + component B: 1 kg).

**Mapecoat I 24** is available in 15 kg units (component A: 12 kg + component B: 3 kg).

### STORAGE

**Mapecoat I 24** can be stored for 24 months in a dry place, away from heat and flame, at temperatures between +5°C and +30°C.

## SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Instructions for the safe use of our products can be found on the latest version of the Safety Data Sheet, available from our website [www.mapei.co.uk](http://www.mapei.co.uk).

When the product reacts it generates considerable heat. After mixing components A and B, it is recommended to apply the product as soon as possible and to never leave the container unguarded until it is completely empty.

PRODUCT FOR PROFESSIONAL USE.

| CHEMICAL RESISTANCE OF MAPECOAT I 24 |                   |           |          |
|--------------------------------------|-------------------|-----------|----------|
|                                      |                   | EXPOSURE  |          |
| CHEMICAL PRODUCTS                    | Concentration (%) | PERMANENT | SPORADIC |
| ACIDS                                |                   |           |          |
| Acetic acid                          | 2,5               | +         | +        |
| Hydrochloric acid                    | 37                | (+)       | +        |
| Chromic acid                         | 20                | —         | —        |
| Citric acid                          | 10                | +         | +        |
| Formic acid                          | 2.5               | +         | +        |
| Lactic acid                          | 2.5               | +         | +        |
| Lactic acid                          | 5                 | +         | +        |

|                                                 |     |     |     |
|-------------------------------------------------|-----|-----|-----|
| Lactic acid                                     | 10  | +   | +   |
| Nitric acid                                     | 25  | –   | (+) |
| Nitric acid                                     | 50  | –   | –   |
| Pure oleic acid                                 | 100 | (+) | +   |
| Phosphoric acid                                 | 50  | +   | +   |
| Phosphoric acid                                 | 75  | +   | +   |
| Sulphuric acid                                  | 1.5 | +   | +   |
| Sulphuric acid                                  | 50  | (+) | +   |
| Sulphuric acid                                  | 96  | –   | –   |
| Tannic acid                                     | 10  | +   | +   |
| Tartaric acid                                   | 10  | +   | +   |
| Oxalic acid                                     | 10  | +   | +   |
| ALKALIS                                         |     |     |     |
| NH <sub>3</sub> in water solution               | 25  | +   | +   |
| Caustic soda                                    | 50  | +   | +   |
| Hypochlorite, Na sol. (active chlorine 6.4 g/l) |     | +   | +   |
| SATURATED SOLUTIONS                             |     |     |     |
| Sodium hyposulphite                             |     | +   | +   |
| Calcium chloride                                |     | +   | +   |
| Ferric chloride                                 |     | +   | +   |
| Sodium chloride                                 |     | +   | +   |
| Sodium chromate                                 |     | +   | +   |
| Sugar                                           |     | +   | +   |
| Aluminium sulphate                              |     | +   | +   |
| Potassium hydroxide                             | 50  | +   | +   |
| Hydrogen peroxide                               | 1   | +   | +   |
| Hydrogen peroxide                               | 10  | +   | +   |
| Sodium bisulphite                               | 10  | +   | +   |
| OILS and FUELS                                  |     |     |     |
| Petrol, fuels                                   |     | +   | +   |
| Oil of turpentine                               |     | +   | +   |
| Diesel oil                                      |     | +   | +   |
| Coal tar oil                                    |     | (+) | +   |
| Olive oil                                       |     | +   | +   |
| Light fuel oil                                  |     | +   | +   |
| Heavy fuel oil                                  |     | +   | +   |
| Petroleum                                       |     | +   | +   |
| SOLVENTS                                        |     |     |     |
| Ethylene glycol                                 |     | +   | +   |
| Glycerine                                       |     | +   | +   |
| Methylcellosolve                                |     | –   | –   |
| Perchloroethylene                               |     | –   | (+) |

|                                                              |  |     |   |
|--------------------------------------------------------------|--|-----|---|
| Carbon tetrachloride                                         |  | (+) | + |
| Trichloroethylene                                            |  | -   | - |
| Chloroform                                                   |  | -   | - |
| Methylene chloride                                           |  | -   | - |
| Tetrahydrofuran                                              |  | -   | - |
| Toluene                                                      |  | (+) | + |
| Carbon sulphide                                              |  | -   | + |
| Benzene                                                      |  | +   | + |
| Trichloroethane                                              |  | (+) | + |
| Xylene                                                       |  | (+) | + |
| Benzol                                                       |  | (+) | + |
| + EXCELLENT RESISTANCE (+) GOOD RESISTANCE - POOR RESISTANCE |  |     |   |

| TECHNICAL DATA (typical values)          |                                   |                           |
|------------------------------------------|-----------------------------------|---------------------------|
| PRODUCT IDENTITY                         |                                   |                           |
|                                          | component A                       | component B               |
| Colour:                                  | neutral, white and RAL colours    | transparent               |
| Consistency:                             | thick paste                       | fluid                     |
| Density (g/cm <sup>3</sup> ):            | 1.43                              | 1.003                     |
| Viscosity (mPa·s):                       | 2,500<br>(5 shaft, 20 rev.)       | 500<br>(2 shaft, 50 rev.) |
| APPLICATION DATA (at +23°C and 50% R.H.) |                                   |                           |
| Mixing ratio:                            | component A : component B = 4 : 1 |                           |
| Density A+B (kg/m <sup>3</sup> ):        | 1,300                             |                           |
| Viscosity A+B (mPa·s):                   | 1,500<br>(3 shaft - 10 rev.)      |                           |
| Colour A+B:                              | neutral, white and RAL colours    |                           |
| Application temperature:                 | from +5°C to +30°C                |                           |
| Pot life:                                | 30'-40'                           |                           |
| Setting time of film:                    | 4-5 hours                         |                           |
| Interval between coats:                  | 6-24 hours                        |                           |
| Final hardening time:                    | 3 days                            |                           |

| ESSENTIAL CHARACTERISTICS IN COMPLIANCE WITH CE-CERTIFICATION EN 1504-2 - Table ZA.1d and ZA.1g (coating C, PI-MC-PR-RC-IR) |                     |                                                                                                     |                     |
|-----------------------------------------------------------------------------------------------------------------------------|---------------------|-----------------------------------------------------------------------------------------------------|---------------------|
| Essential characteristics                                                                                                   | EN 1504 Test Method | Requirements                                                                                        | Product performance |
| Abrasion resistance (TABER test) Note: Testing methods according to EN 13813 for flooring systems are also acceptable       | EN ISO 5470-1       | Loss in weight less than 3000 mg after 1000 cycles with an H22 abrasive disk with a load of 1,000 g | 900 mg              |

|                                                                                                                                                                                                                                                                                                                                                                              |                                                    |                                                                                                                                                                                                                                                                                                                           |                                                                            |
|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------|
| Permeability to CO <sub>2</sub>                                                                                                                                                                                                                                                                                                                                              | EN 1062-6 (sample treated according to EN 1062-11) | Permeability to CO <sub>2</sub> S <sub>d</sub> > 50 m                                                                                                                                                                                                                                                                     | S <sub>d</sub> 1255 m                                                      |
| Permeability to water vapour                                                                                                                                                                                                                                                                                                                                                 | EN ISO 7783-1-2                                    | Class I: S <sub>d</sub> < 5 m (permeable to water vapour) Class II: 5 m ≤ S <sub>d</sub> ≤ 50 m<br>Class III: S <sub>d</sub> > 50 m (not permeable to water vapour)                                                                                                                                                       | Class III                                                                  |
| Capillary absorption and permeability to water                                                                                                                                                                                                                                                                                                                               | EN 1062-3                                          | W < 0.1 kg/m <sup>2</sup> ·h <sup>0,5</sup>                                                                                                                                                                                                                                                                               | 0,02 kg/m <sup>2</sup> ·h <sup>0,5</sup>                                   |
| Resistance to thermal shock (1x)                                                                                                                                                                                                                                                                                                                                             | EN 13687-5                                         | ≥ 2 MPa                                                                                                                                                                                                                                                                                                                   | 3.5 MPa                                                                    |
| Resistance to severe chemical attack<br>Class I: 3 days with no pressure<br>Class II: 28 days with no pressure<br>Class III: 28 days with pressure<br>We recommend using test liquids for the 20 classes indicated in EN 13529, which cover all types of the most commonly-used chemical agents. Other test liquids may be agreed upon between those interested in the tests | EN 13529                                           | Group 9 (class II with bubbles)<br>Group 10 (class II)<br>Group 11 (class II)<br>Group 12 (class II)<br>Reduction of hardness less than 50% when measured according to the Buchholz method (EN ISO 2815) or the Shore method (EN ISO 868), 24 hours after removing the coating material from immersion in the test liquid | No variation in performance.<br>Bubbles with 10% acetic acid after 28 days |
| Resistance to impact measured on MC (0.40) coated concrete samples according to EN 1766.<br>Note: The forecast thickness and impact load influence which class is chosen                                                                                                                                                                                                     | EN ISO 6272-1                                      | No cracks or delamination after loading<br>Class I: ≥ 4 Nm<br>Class II: ≥ 10 Nm<br>Class III: ≥ 20 Nm                                                                                                                                                                                                                     | Class I                                                                    |
| Direct traction adherence test Reference substrate: MC (0.4) as specified in EN 1766 curing:<br>– 28 days for single component systems containing concrete and PCC systems;<br>– 7 days for systems with reactive resin                                                                                                                                                      | EN 1542                                            | Average (N/mm <sup>2</sup> )<br>Cracking or flexible systems with no traffic: ≥ 0.8 (0,5) <sup>b)</sup><br>with traffic: ≥ 1.5 (1,0) <sup>b)</sup><br>Rigid systems <sup>c)</sup> with no traffic: ≥ 1.0 (0,7) <sup>b)</sup><br>with traffic: ≥ 2.0 (1,0) <sup>b)</sup>                                                   | 3.89 N/mm <sup>2</sup>                                                     |
| Reaction to fire:                                                                                                                                                                                                                                                                                                                                                            | EN 13501-1                                         | Euroclasses                                                                                                                                                                                                                                                                                                               | B <sub>FL</sub> - s1<br>C - s1 - d0                                        |

## WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website [www.mapei.co.uk](http://www.mapei.co.uk)

## LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

330-06-2022 (UK)

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

