

SIGMAFAST™ 205

DESCRIPTION

Two-component, high-build, polyamide-cured zinc phosphate epoxy primer/coating

PRINCIPAL CHARACTERISTICS

- General-purpose epoxy primer/coating for atmospheric conditions
- Fast-curing
- Suitable for the protection of steel and concrete
- Easy application by airless spray
- Recoatable with most two-component epoxy and polyurethane coatings
- Tough, with long-term flexibility

COLOR AND GLOSS LEVEL

- A wide range of colors and MIO light available
- Semi-gloss

Notes:

- Epoxy coatings will chalk and fade upon exposure to sunlight, elevated temperatures, or chemical exposure. Discoloration and normal chalking do not impact performance. Light colors will darken over time. Some batch-to-batch variation in color is to be expected. Color matches are approximate.
- The addition of a UV stable topcoat should be considered when using epoxy coatings in cosmetic areas

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.7 lb/US gal)
Volume solids	70 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 224.0 g/kg UK PG 6/23(92) Appendix 3: max. 322.0 g/l (approx. 2.7 lb/US gal) EUR Directive: 2004/42/IIA(j)(500) 411 g/l
Recommended dry film thickness	75 - 150 µm (3.0 - 6.0 mils) depending on system
Theoretical spreading rate	9.3 m ² /l for 75 µm (374 ft ² /US gal for 3.0 mils) 4.7 m ² /l for 150 µm (187 ft ² /US gal for 6.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 4 hours Maximum: 6 months
Full cure after	3 days



SIGMAFAST™ 205

Data for mixed product

Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry
-------------------	--

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)

Concrete

- Dried for at least 28 days in good ventilation conditions
- Moisture content should not exceed 4.5%
- Concrete must be free from laitance and any contamination
- Rough surface; eventually abraded by power tool or diamond abrading tool

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 75:25 (3:1)

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Thinner should be added after mixing the components

Induction time

Mixed product induction time	
Mixed product temperature	Induction time
Below 10°C (50°F)	10 minutes
Above 10°C (50°F)	None

SIGMAFAST™ 205

Pot life

6 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

Air spray**Recommended thinner**

THINNER 91-92

Volume of thinner

5 - 15%, depending on required thickness and application conditions

Nozzle orifice

1.5 - 3.0 mm (approx. 0.060 - 0.110 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray**Recommended thinner**

THINNER 91-92

Nozzle orifice

Approx. 0.48 mm (0.019 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller**Recommended thinner**

THINNER 91-92

Volume of thinner

0 - 5%

Cleaning solvent

THINNER 90-53

SIGMAFAST™ 205

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
75 µm (3.0 mils)	9.3 m ² /l (374 ft ² /US gal)
100 µm (4.0 mils)	7.0 m ² /l (281 ft ² /US gal)
150 µm (6.0 mils)	4.7 m ² /l (187 ft ² /US gal)

Overcoating interval for DFT up to 75 µm (3.0 mils)						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
various two-pack epoxy and polyurethane coatings	Minimum	12 hours	6 hours	3 hours	2 hours	1 hour
	Maximum	6 months	6 months	6 months	6 months	6 months

Overcoating interval for DFT up to 150 µm (6.0 mils)						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
various two-pack epoxy and polyurethane coatings	Minimum	12 hours	6 hours	4 hours	3 hours	2 hours
	Maximum	6 months	6 months	6 months	6 months	6 months

Note: Surface should be dry and free from any contamination

Curing time for DFT up to 75 µm (3.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	12 hours	16 hours	7 days
10°C (50°F)	7 hours	10 hours	5 days
20°C (68°F)	3 hours	5 hours	3 days
30°C (86°F)	1.5 hours	3 hours	60 hours
40°C (104°F)	1 hour	2 hours	36 hours

Curing time for DFT up to 150 µm (6.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	14 hours	18 hours	8 days
10°C (50°F)	8 hours	12 hours	6 days
20°C (68°F)	4 hours	6 hours	4 days
30°C (86°F)	2 hours	4 hours	3 days
40°C (104°F)	1 hour	3 hours	48 hours

Note: Adequate ventilation must be maintained during application and curing



SIGMAFAST™ 205

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	10 hours
20°C (68°F)	6 hours
30°C (86°F)	3 hours

SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- EXPLANATION TO PRODUCT DATA SHEETS INFORMATION SHEET 1411

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

