

## PRODUCT DATA SHEET

# Sikalastic® D-15 RoofPro Advanced

High performance polyurethane liquid applied waterproofing membrane

## PRODUCT DESCRIPTION

Sikalastic® D-15 RoofPro Advanced is a 1-part polyurethane, reinforced, cold-applied liquid membrane. It provides a flexible, seamless waterproofing solution using Sika's unique i-Cure technology.

## USES

Designed for the following waterproofing applications:

- Roof waterproofing for new construction and refurbishment projects
- Unreinforced waterproofing system for profiled metal roofs
- Reinforced waterproofing of flat and pitched roof structures
- Waterproofing structures with numerous details such as penetrations, drains, roof lights and complex geometry
- Waterproofing existing substrates of concrete, bituminous felt and coatings, brick, stone, asbestos cement, metal, wood, unglazed ceramic tiles
- For exterior use only

Sikalastic® D-15 RoofPro Advanced may only be used by experienced professionals.

## CHARACTERISTICS / ADVANTAGES

- 1-Part ready to use
- Low maintenance
- Seamless
- Easy and quick application by brush, roller or spray
- Suitable for trafficable areas
- Vapour permeable
- Good UV resistance and colour stability
- Retains flexibility at low temperatures
- Cold applied - requires no heat or flame
- Moisture triggered technology develops early rain resistance
- Good elastic properties
- Low temperature application > +2 °C

## APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to European Technical Assessment, based on ETAG 005 Part 1 and Part 6
- Fire Testing according to ENV 1187: Test Report No. 19823F, 19823K, 19823B, 19750A, 19750D, 19750G
- Fire Testing EN 13501-1, Sikalastic® D-15 RoofPro Advanced,

## PRODUCT INFORMATION

Chemical Base	Elastomeric aliphatic polyurethane
Packaging	15 Litre tin
Colour	Light Grey (RAL 7035), Slate Grey (RAL 7015)
Shelf Life	12 months from date of production
Storage Conditions	The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.
Density	~1,26 kg/l (EN ISO 2811-1)
Solid content by mass	~77 % (+23 °C / 50 % r.h.) (EN ISO 3251)

<b>Solid content by volume</b>	~71 % (+23 °C / 50 % r.h.)	(EN ISO 3251)
<b>Tensile Strength</b>	Reinforced	~13 N/mm <sup>2</sup>
	Unreinforced	~6 N/mm <sup>2</sup>
<b>Tear Strength</b>	~26 N/mm	(ISO 527-1/3)
<b>External Fire Performance</b>	Broof (t1); Broof (t4)	(ENV-1187)
<b>Reaction to Fire</b>	Euroclass E	(EN13501-1)
<b>Chemical Resistance</b>	Resistant to many chemicals. Contact Sika Technical Services for additional information.	
<b>Thermal Resistance</b>	-20 °C to +80 °C	
<b>Solar Reflectance</b>	Initial: 0,87	
<b>Thermal Emittance</b>	Initial: 0,88	
<b>Solar Reflectance Index</b>	Initial: 110	
<b>Service Temperature</b>	-20 °C min. / +80 °C max.	

#### System Structure

Note: For detailed reinforcement information refer to the Sika Method Statement: Sikalastic® D-15 RoofPro Advanced

Note: These figures are theoretical and do not include for any additional material required due to surface porosity, surface profile, variations in level and wastage etc.

#### Flat Roof Waterproofing Only - 20 year expected durability\*

The build-up in the table corresponds to a reinforced waterproofing kit for flat and pitched roofs.

Layer	Product	Consumption
1. Primer	Depending on Substrate	Refer to the primer Product Data Sheet
2. Base Coat	Sikalastic® D-15 RoofPro Advanced	~1,0 l/m <sup>2</sup>
3. Reinforcement	Sika® Reemat Premium	-
4. Top Coat	Sikalastic® D-15 RoofPro Advanced	~0,75 l/m <sup>2</sup>
<b>Gutter System</b>		
1. Primer	Depending on the substrate	Refer to the primer Product Data Sheet
2. Base Coat	Sikalastic® D-15 RoofPro Advanced	~1,0 l/m <sup>2</sup>
3. Reinforcement	Sika® Reemat Premium	-
4. Top Coat	Sikalastic® D-15 RoofPro Advanced	~1,0 l/m <sup>2</sup>

**Flat Roof Waterproofing Only - 25 year expected durability\***

The build-up in the table corresponds to a reinforced waterproofing kit for flat and pitched roofs.

Layer	Product	Consumption
1. Primer	Depending on Substrate	Refer to the primer Product Data Sheet
2. Base Coat	Sikalastic® D-15 RoofPro Advanced	~1,0 l/m <sup>2</sup>
3. Reinforcement	Sika® Reemat Preemium	-
4. Top Coat	Sikalastic® D-15 RoofPro Advanced	~1,0 l/m <sup>2</sup>

**Gutter System**

1. Primer	Depending on the substrate	Refer to the primer Product Data Sheet
2. Base Coat	Sikalastic® D-15 RoofPro Advanced	~1,25 l/m <sup>2</sup>
3. Reinforcement	Sika® Reemat Preemium	-
4. Top Coat	Sikalastic® D-15 RoofPro Advanced	~1,0 l/m <sup>2</sup>

**Asbestos & Profiled Metal Roof Sheets - Waterproofing Only - 10 Year expected durability\***

The build-up in the table corresponds to a locally reinforced waterproofing kit for metal and asbestos roofs.

Layer	Product	Consumption
1. Primer	Depending on Substrate	Refer to the primer Product Data Sheet
2. Base Coat	Sikalastic® D-15 RoofPro Advanced	~0,5 l/m <sup>2</sup>
3. Localised reinforcement	Refer to Application Guidelines	-
4. Top Coat	Sikalastic® D-15 RoofPro Advanced	~0,5 l/m <sup>2</sup>

**Waterproofing Only - 15 Year expected durability\***

The build-up in the table corresponds to a locally reinforced waterproofing kit for metal and asbestos roofs.

Layer	Product	Consumption
1. Primer	Depending on Substrate	Refer to the primer Product Data Sheet
2. Base Coat	Sikalastic® D-15 RoofPro Advanced	~0,75 l/m <sup>2</sup>
3. Localised Reinforcement	Refer to Application Guidelines	-
4. Top Coat	Sikalastic® D-15 RoofPro Advanced	~0,75 l/m <sup>2</sup>

\*Expected durability is defined within the associated BBA Agrément certificate and is not a guarantee period

<b>Dry film thickness</b>	ETA-20/0073 waterproofing kit for all flat roof types	~1,5 mm
	ETA-20/0073 waterproofing kit for all metal roof types	~0,7 mm
<b>System Performance</b>	ETA-20/0073 waterproofing kit for all flat roof types	W3 / M and S / P3-P4 / S1-S4 / TL4 – TH4
	ETA-20/0073 waterproofing kit for all metal roof types	W2 / M and S / P3 / S1-S4 / TL3 - TH3

Ambient Air Temperature	+2 °C min. / +30 °C max.																							
Relative Air Humidity	20 % min. / 85 % max.																							
Substrate Temperature	+2 °C min. / +30 °C max.																							
Dew Point	Beware of condensation. The substrate and uncured applied product must be at least +3 °C above dew point to reduce the risk of condensation or blooming on the surface of the applied product. Metal surfaces will be more prone to temperature fluctuations occurring and wind chill effects.																							
Substrate Moisture Content	≤ 4% parts by weight The following test methods can be used to determine the substrate moisture content: <ul style="list-style-type: none"><li>▪ Sika®-Tramex meter</li><li>▪ No rising moisture must be present according to ASTM (Polyethylenesheet).</li></ul>																							
Substrate Pre-Treatment	Important: Other substrates must be tested for their compatibility. To ensure compatibility, carry out preliminary trials. Important: Adhesion and compatibility suitability must be verified practically on site before commencing contract. Note: For consumption rates and waiting time / overcoating, refer to the individual Product Data Sheet of the appropriate primer. <table><tr><td>Substrate</td><td>Primer</td></tr><tr><td>Cementitious, concrete, brick, stone, ceramic tiles (unglazed)</td><td>Sika® Concrete Primer LO Sika® Bonding Primer</td></tr><tr><td>Metals: Ferrous or galvanised, lead, copper, aluminium, brass, stainless steel</td><td>Sikalastic® Metal Primer</td></tr><tr><td>Bituminous felt &amp; coating</td><td>Sikalastic® Metal Primer</td></tr><tr><td>Timber</td><td>Timber based roof decks require a complete layer of Sikalastic® Carrier. For small exposed sections, use Sika® Concrete Primer LO or Sika Bonding Primer.</td></tr><tr><td>Paint coatings</td><td>Subject to adhesion and compatibility tests</td></tr><tr><td>Existing Sikalastic® D-15 RoofPro Advanced system</td><td>Sika® Reactivation Primer</td></tr></table>				Substrate	Primer	Cementitious, concrete, brick, stone, ceramic tiles (unglazed)	Sika® Concrete Primer LO Sika® Bonding Primer	Metals: Ferrous or galvanised, lead, copper, aluminium, brass, stainless steel	Sikalastic® Metal Primer	Bituminous felt & coating	Sikalastic® Metal Primer	Timber	Timber based roof decks require a complete layer of Sikalastic® Carrier. For small exposed sections, use Sika® Concrete Primer LO or Sika Bonding Primer.	Paint coatings	Subject to adhesion and compatibility tests	Existing Sikalastic® D-15 RoofPro Advanced system	Sika® Reactivation Primer						
Substrate	Primer																							
Cementitious, concrete, brick, stone, ceramic tiles (unglazed)	Sika® Concrete Primer LO Sika® Bonding Primer																							
Metals: Ferrous or galvanised, lead, copper, aluminium, brass, stainless steel	Sikalastic® Metal Primer																							
Bituminous felt & coating	Sikalastic® Metal Primer																							
Timber	Timber based roof decks require a complete layer of Sikalastic® Carrier. For small exposed sections, use Sika® Concrete Primer LO or Sika Bonding Primer.																							
Paint coatings	Subject to adhesion and compatibility tests																							
Existing Sikalastic® D-15 RoofPro Advanced system	Sika® Reactivation Primer																							
Pot Life	Note: The material in opened containers must be applied before a surface skin occurs. Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity. ~1–2 hours																							
Applied Product Ready for Use	Important: The impact of heavy rain or rain showers can physically mark or damage the membrane in its liquid state. Note: Application at higher than recommended film thicknesses may result in a prolonged “soft” feel to the coating. This will eventually cure and harden. Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity. <table><tr><td>Ambient conditions</td><td>Rain resistant</td><td>Touch Dry</td><td>Full Cure</td></tr><tr><td>+2°C / 50 % r.h.</td><td>~12 hours</td><td>~20 hours</td><td>&gt;24 hours</td></tr><tr><td>+10°C / 50 % r.h.</td><td>~9 hours</td><td>~15 hours</td><td>~24 hours</td></tr><tr><td>+20°C / 50 % r.h.</td><td>~6 hours</td><td>~10 hours</td><td>~18 hours</td></tr><tr><td>+30°C / 50 % r.h.</td><td>~4 hours</td><td>~6 hours</td><td>~14 hours</td></tr></table>				Ambient conditions	Rain resistant	Touch Dry	Full Cure	+2°C / 50 % r.h.	~12 hours	~20 hours	>24 hours	+10°C / 50 % r.h.	~9 hours	~15 hours	~24 hours	+20°C / 50 % r.h.	~6 hours	~10 hours	~18 hours	+30°C / 50 % r.h.	~4 hours	~6 hours	~14 hours
Ambient conditions	Rain resistant	Touch Dry	Full Cure																					
+2°C / 50 % r.h.	~12 hours	~20 hours	>24 hours																					
+10°C / 50 % r.h.	~9 hours	~15 hours	~24 hours																					
+20°C / 50 % r.h.	~6 hours	~10 hours	~18 hours																					
+30°C / 50 % r.h.	~4 hours	~6 hours	~14 hours																					

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

Installation work must only be carried out by Sika trained and approved contractors, experienced in this type of application.

- Do not use for indoor applications.
- Do not apply on substrates with rising moisture or are not stable. Do not dilute with any solvent.
- Do not apply near to running air intakes of air conditioning units. Switch off units and seal intakes before applying.
- All areas requiring an anticorrosive protection system must be applied directly to a prepared bright metal finish.

## ECOLOGY, HEALTH AND SAFETY

### EQUIPMENT

Select the most appropriate equipment required for the project:

#### Substrate preparation equipment

- Abrasive blast cleaning / planing / scarifying or grinding equipment.
- Manual or mechanical wire brushes
- High pressure power washer

For other types of preparation equipment, contact Sika Technical Services

#### Mixing Equipment

- Electric single paddle mixer (300–400 rpm) with spiral paddle
- For other types of preparation equipment, contact Sika Technical Services

#### Application Equipment

- Brush
- Roller
- Airless spray

### SUBSTRATE PREPARATION

- The supporting structure must be of sufficient structural strength to apply all new and existing layers of the roof build-up. Complete roof system must be designed and secured against wind uplift loadings.
- Suitable substrates: Cementitious, concrete, bituminous felt and coatings, brick, stone, asbestos cement, metal, wood, unglazed ceramic tiles

#### General

All contamination such as dust, loose and friable material that could affect final finish or reduce adhesion, must be completely removed from all surfaces before application of the product or subsequent products, preferably by industrial vacuuming equipment.

## MIXING

- Sikalastic® D-15 RoofPro Advanced is supplied ready for use.
- Before application, mix for at least 2 minutes or until the liquid and all the coloured pigment have achieved a uniform colour.

## APPLICATION

Asbestos & Profiled Metal Roof Sheets - Localised Reinforcement for Roof Areas Only

### Sheet End Laps

Prepare and prime the corrugate roof sheet as appropriate. Apply 6" (152.4mm) wide of Sika® Joint Tape SA to prepared substrate.

Remove 4–6" (10.2–15.2 cm) of release liner from underside of the Sika Joint Tape SA and position the tape centrally across the lap joint of the top and bottom sheet, and pressing firmly into place.

Continue to remove release liner, whilst moving across the lap joint.

Be careful to follow the profile of the metal sheet and ensure full and even contact.

Ensure that the tape overlaps any end lap fixings by at least 25mm. Where this cannot be achieved, a separate piece of 3" (76.2mm) should be used to reinforce each fixing.

Once in-place, always apply additional pressure to the surface to fully activate the bonding process, compress any creases and remove any trapped air. Use a hard roller for best results.

### Side Laps

Apply 6" (152.4mm) wide Sika® Joint Tape SA to the prepared substrate.

Remove 4–6" (10.2–15.2 cm) of release liner from the underside of the Sika® Joint Tape SA.

Position the tape centrally across the joint, and press into place. Continue to remove release liner, whilst moving down the joint and pressing firmly onto the substrate surface.

Ensure that the tape overlaps any side lap fixings by at least 25mm. Where this cannot be achieved, a separate piece of 3" (76.2mm) should be used to reinforce each fixing.

Once in-place, always apply additional pressure to the surface to fully activate the bonding process, compress any creases and remove any trapped air. Use a hard roller for best results.

**Tape Embedment:** In any application, a light coat of Sikalastic® D-15 RoofPro Advanced must be applied to the surface and edges of Sika Joint Tape SA® and allowed to cure. The purpose of this is to waterproof the surface of the tape and ensure that the surface of the fabric is fully embedded in the main coating. This can be applied using a roller or brush.

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

### **Gutter Joints - Metal Gutters - Bolted Joints/Fixings**

Bridge each bolt head/fixing with Sika Flexistrip (minimum 50mm squares) by first removing the backing paper and applying light pressure to the patch edges to fix.

Encapsulate each fixing/joint detail using Sika Reemat Premium patches, cut to requirements and bedded in Sikalastic® D-15 RoofPro Advanced applied at a minimum wet film thickness of 1000 microns. Allow to dry before continuing with the overall waterproofing. Apply the fully reinforced system through the metal gutter as specified.

### **Gutter Joints - Metal Gutters - Bond Break**

Introduce a 'bond break' at each gutter joint by first laying 50mm (minimum width) low tack de-bonding tape centred on the joint.

Apply a 'stripe' coat (200mm wide) of Sikalastic® D-15 RoofPro Advanced to each seam/joint at a minimum wet film thickness of 1000 microns and whilst wet, Sika Flexitape Heavy (150mm) using a loaded brush to obliterate the tape.

Allow to dry before continuing with the top coats.

### **CLEANING OF TOOLS**

Clean all tools and application equipment with Thinner C or xylene immediately after use. Hardened material can only be removed mechanically or with a proprietary paint stripper.

### **LOCAL RESTRICTIONS**

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### **SIKA LIMITED**

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited



#### **Product Data Sheet**

Sikalastic® D-15 RoofPro Advanced  
February 2021, Version 01.01  
020915205000000084

SikalasticD-15RoofProAdvanced-en-GB-(02-2021)-1-1.pdf