

# UVILUX SEALER 1453-02

## UV-Sealer

UV-curing combi-lacquer. Industrial surface treatment of wood and furniture parts. Is suitable as sealer as well as lacquer.



UVILUX SEALER is especially developed as a sealer and is therefore easy to sand. Used as lacquer the cured surface provides hard surface with mechanical and chemical resistance.

FURNITURE TEST – Field of application:

Chairs/beds/shelves: Extra high demands

Tables: High demands

Less exposed surfaces: Extra high demands



## TECHNICAL DATA

<b>Fields of application</b>	Ceilings, Floors, Furniture, Kitchen, Mouldings, Panels, Stairs, Interior doors
<b>Recommended substrate</b>	HDF, Masonite, MDF, Hardwood, Softwood
<b>Solids</b>	Approx. 100% by weight
<b>Total mass of solids</b>	Approx. 1298 g/l
<b>Viscosity</b>	Approx. 110 s DIN cup 6 at +20°C.
<b>Volatile organic compound (VOC)</b>	See safety data sheet.
<b>Gloss (60°)</b>	Semi-matt
<b>Thinner</b>	The product is delivered ready for use.
<b>Density</b>	Approx. 1.30 kg/l
<b>Storage</b>	Should not be exposed to temperatures above 40°C. Should not be exposed to direct sunlight. Must not freeze. The storage stability is shown on the label. Store in a tightly closed container.

## DIRECTION FOR USE

<b>Application method</b>	Smooth roller
---------------------------	---------------

## Drying time

UVILUX SEALER 1453-02 HY 0020 CLEAR							
Semi curing				Full curing			
Hg		Ga		Hg		Ga	
Energy UVB mJ/cm <sup>2</sup>	Peak mW/cm <sup>2</sup>	Energy UVV mJ/cm <sup>2</sup>	Peak mW/cm <sup>2</sup>	Energy UVB mJ/cm <sup>2</sup>	Peak mW/cm <sup>2</sup>	Energy UVV mJ/cm <sup>2</sup>	Peak mW/cm <sup>2</sup>
60	200			100	300		

  

UVILUX SEALER 1453-02 TS 20799 WHITE							
Semi curing				Full curing			
Hg		Ga		Hg		Ga	
Energy UVB mJ/cm <sup>2</sup>	Peak mW/cm <sup>2</sup>	Energy UVV mJ/cm <sup>2</sup>	Peak mW/cm <sup>2</sup>	Energy UVB mJ/cm <sup>2</sup>	Peak mW/cm <sup>2</sup>	Energy UVV mJ/cm <sup>2</sup>	Peak mW/cm <sup>2</sup>
300	300	760	650	150	300	380	650

## Drying methods

UV lamps.

## Cleaning

TEKNOSOLV 1187-11 or TEKNOSOLV 1129-11.

## HEALTH AND SAFETY

### Safety and precaution measures

See safety data sheet.

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.