

AQUATOP 2600-22

Topcoat for spray application

AQUATOP 2600-22, a water-borne industrial topcoat for wood designated for exterior use such as windows and doors.



TECHNICAL DATA

Fields of application	Cladding boards, Conservatories, Exterior doors, Windows, Window shutters
Recommended substrate	Hardwood, Modified wood, Softwood
Solids	32-36% by volume 35-48% by weight
Volatile organic compound (VOC)	See safety data sheet.
Theoretical spreading rate	3-7 m ² /l
Colours	Base 1, 2, 3 and base T (white, opaque and translucent colours).
Tinting system	Teknocolour; Teknoshade
Gloss (60°)	Semi-matt
Storage	Storage temperature is +5°C - +30°C. Shelf life in unopened containers: See "Best before date" on the label. Keep containers tightly closed after use.
Packaging	Available in a range of standard pack sizes.

DIRECTION FOR USE

Surface preparation	The wood must be free from wood dust and contamination. The moisture content of the wood should be approx. 13% and should not exceed 15%. Pretreatment is required for wood substrates not meeting Durability Class 3, EN 350:2016. Teknos has a range of preservative products meeting the requirements of EN 599-1, please contact Teknos for further guidance.		
Application method	Airless spraying, Air-assisted airless spraying, Electrostatic spraying		
Application	Nozzle	Pressure	Air support
	Airless flat 0.28 mm	100-110 bar	
	Air assisted airless flat 0.28 mm	80-100 bar	1.0-1.5 bar
Application conditions	Stir thoroughly before use.		

Application conditions	Stir thoroughly before use. Optimum temperature for products and surroundings: +18°C - +22°C. Optimum relative air humidity: Approx. 50%. Wet film range 150-300 µm.
-------------------------------	---

Thinning	The product is delivered ready for use.
Drying time	+23 °C / 50% RH
- dry to handle	2-3 hours
- fit for sanding and overcoating	3-4 hours
	The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation, and film thickness. The drying time can be reduced using special drying systems to force drying.
Coating system	AQUATOP 2600-22 is part of a coating system where the dry film thickness should be > 100 µm. If the parts are exposed to the influence of the weather never use colourless as the final treatment.
Cleaning	Water.

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
---------------------------------------	------------------------

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.