

AQUATOP 2600-01

Air drying topcoat

Opaque, air drying, and water-borne topcoat for surface coating of primed wood, primed metal, and tarpaulins.

Good external durability. No blocking tendency. Elastic and micro porous. Good adhesion to wood. Can be applied in wet film thickness of 200 - 250 µm. Good water resistance. Suitable under all climatic conditions in Europe.



TECHNICAL DATA

Recommended substrate	Metal, Wood
Solids	Approx. 44% by volume Approx. 55% by weight
Total mass of solids	Approx. 697 g/l
Volatile organic compound (VOC)	See safety data sheet.
Theoretical spreading rate	9-11 m ² /l
Colours	Danish Green DG 15 NIR, Black.
Gloss (60°)	Matt
Storage	The storage stability is shown on the label. Store in a tightly closed container. Must not freeze.

DIRECTION FOR USE

Surface preparation	The surface to be treated must be free of dust and contamination.		
Priming	AQUAPRIMER 2900-05 in colour code TS0482, INERTA PRIMER 3210-01 in colour code TS0482,		
Application method	Airless spraying, Air-assisted airless spraying, Brush, Roller		
Application	Equipment	Thinner	Suggested viscosity DIN-cup 4 mm 20 °C
	Airless	Undiluted	
	Airless/Air-assisted	Undiluted	
	Conventional spraying	Water	60-80 s
	Brush/roller	Undiluted	
Application conditions	Stir thoroughly before use. When coating and curing the relative air humidity must be 40 – 60 %. Temperature: 15 – 25 °C. Dry film: 40 µm Wet film: 100 µm		

Drying time	+18-23°C / 50% RH
-touch dry	30 min. (ISO 1517)
-dry to handle	1-2 h (ISO 3678)

The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation, and film thickness.

Overcoatable	Re-coating is possible after 2 - 3 hours, dependent upon the film thickness, temperature, and air humidity and circulation.
---------------------	---

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
---------------------------------------	------------------------

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.