

TECHNICAL DATASHEET

Issue date:
October 2020

SELEMIX® 1K SYNTHETIC URETHANE TOPCOAT 7-630

PRODUCT DESCRIPTION

Selemix 7-630 1K Synthetic Urethane Topcoat is a high gloss 1K synthetic finish for solid colours and single-layer metallic finishes.

It is compatible with *Selemix Fast Dry* primers, giving a durable paint system. It has a very high gloss finish with good durability. Application can be by conventional or air-assisted airless spray.

It is suitable for the coating of machinery, agricultural and construction equipment, and many other industrial painting applications where a high gloss finish is required.

PRODUCTS

7-630 *Selemix 1K Synthetic Urethane Topcoat*
 NPxx *Selemix NP Tinters*

Thinners:

1-610 Synthetic Thinner
 1-215 Nitrocellulose Thinner
 1-205 Aromatic Free Thinner

SUBSTRATES AND PREPARATION



Painted Surfaces
Polyurethane or
Polyester Fillers

Machine sand with P320-400 discs and degrease






Selemix 1K primers :

Refer to Primer TDS for recoat time




Apply only on a clean and dry surface with a temperature above the dew point to avoid condensation. In confined spaces, provide adequate ventilation during application and drying.

MIXING

Thoroughly mix paint before activating and check colour before use

	Features	Conventional	Air-Assisted Airless
	By Weight: 7-630 Topcoat 1-610/1-215/1-205 Thinner	1000 250-350	1000 100-200
	By Volume: 7-630 Topcoat 1-610/1-215/1-205 Thinner	7 2 - 3 (30-40%)	10 1 - 2 (10-20%)
	Viscosity (at 20°C): Pot Life (at 20°C):	18-22 secs DIN4 Unlimited	30-50 secs DIN4 Unlimited

APPLICATION

	Features	Conventional	Air-Assisted Airless
	Spraygun setup: Air Pressure: Fluid Pressure:	Nozzle: Gravity: 1.3-1.4mm Suction: 1.6-1.8mm Pressure feed: 0.85-1.2mm HVLP: 2 Bar Standard: 2-3 Bar N/A	Nozzle: 9-11 thou 0.23-0.28mm 2.5 Bar 100-120 Bar
	Number of coats: Flash-off between coats:	2 10-15 mins	2 10-15 mins
	Drying: Wet Film Thickness: Dry Film Thickness:	Air dry 100-120 microns 40-50 microns	Air dry 100-120 microns 40-50 microns

DRYING TIMES



at 20°C

Dust Free:
 Touch Free:
 Tape Free:
 Handleable:
 Hard Dry:
 Overcoating time:

10-15 mins

1-2 hours

16 hours

4-5 hours

48-72 hours

Minimum: 2 hours

Maximum: 10 days by itself without sanding

Lower temperature or film thickness higher than 50µm
 will extend drying times

TECHNICAL DATA

Based on ready-for-use mixed paint
 including thinner:

VOC (g/L):

Solid content (weight):

Solid content (volume):

Solvent content (weight):

Specific gravity (Ready for use)

535-619 g/L (depending on colour and dilution)

41-49 %

30-39 %

51-59 %

0.96-1.05 Kg/L

Theoretical coverage:

Gloss:

5.9-7.8 m²/L at 50 microns DFT

High Gloss

Note on Paint Mixing:

When mixing colours, it is recommended that binders
 and toners are weighed out first and mixed well before
 the addition of driers

PRODUCT CODES AND DESCRIPTIONS

Selemix Code	Short Code	Product Description	Packsize	
1.776.3000/E3.25K	7-630	1K Synthetic Urethane Topcoat	3.25	Kg
1.911.5610/E5	1-610	Synthetic Thinner	5	Lt
1.921.3215/E5	1-215	Nitrocellulose Thinner	5	Lt
1.991.1205/E25	1-205	Aromatic Free Thinner	25	Lt

HEALTH AND SAFETY

For comprehensive Health, Safety and Environmental advice, please refer to the relevant Material Safety Data Sheets and Product can labels.

THIS PRODUCT IS FOR PROFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

FOR FURTHER INFORMATION PLEASE CONTACT:

Selemix Customer Service and Sales Group
Needham Road
Stowmarket, Suffolk
IP14 2AD, England
Tel: 01449 771771