

## TECHNICAL DATASHEET

Issue date:  
Feb 2020

# SELEMIX® 2K POLYURETHANE UHS TOPCOAT 7-550

## PRODUCT DESCRIPTION

*Selemix 7-550 2K Polyurethane UHS Topcoat* is a 2-pack polyurethane finish for solid colours and single-layer metallic finishes. It has high solids and a low VOC.

It is compatible with *Selemix Epoxy* and *Polyurethane* primers, giving a durable and hard wearing paint system. It has a high gloss finish (>90%) with excellent durability and UV stability.

It is suitable for the coating of trailers, machinery, agricultural and construction equipment, and many other industrial painting applications where a very durable, high gloss finish is required with a low VOC.

## PRODUCTS

7-550                    *Selemix Polyurethane UHS Topcoat*  
 NPxx                    *Selemix NP Tinters*

### Hardener:

9-075                    Direct HS Hardener

### Thinners:

1-480                    Direct PUR Thinner

1-470                    Slow Direct Thinner

## SUBSTRATES AND PREPARATION



Painted Surfaces  
Polyurethane or  
Polyester Fillers

Machine sand with P320-400 discs and degrease






*Selemix Epoxy Primers*  
or *PU Primers*

Refer to Primer TDS for recoat time




Apply only on a clean and dry surface with a temperature above the dew point to avoid condensation. In confined spaces, provide adequate ventilation during application and drying.

## MIXING

Thoroughly mix paint before activating and check colour before use

	Features	Conventional
	<b>By Weight:</b> 7-550 Topcoat 9-075 Hardener 1-480/1-470 Thinner	1000 400 100 - 200
	<b>By Volume:</b> 7-550 Topcoat 9-075 Hardener 1-480/1-470 Thinner	2.5 1 0.1 – 0.5 (5-20%)
	Viscosity (at 20°C): Pot Life (at 20°C):	23-25 secs DIN4 2 hours

## APPLICATION

	Features	Conventional
	Spraygun setup:  Air Pressure: Fluid Pressure:	Nozzle: Gravity: 1.3-1.4mm Suction: 1.6-1.8mm Pressure feed: 0.85-1.2mm  HVLP: 2 Bar Standard: 2-3 Bar N/A
	Number of coats: Flash-off between coats:	2 10-15 mins
	Drying:  Flash-off before bake: Wet Film Thickness: Dry Film Thickness:	Air dry or bake at 60°C for 45 mins  20 mins 100-140 microns 50-70 microns

## DRYING TIMES



at 20°C

Dust Free:	10-15 mins
Touch Free:	1-2 hours
Tape Free:	10-12 hours
Handleable:	4-6 hours
Hard Dry:	10-12 hours or after bake
Overcoating time:	Minimum: 16 hours Maximum: 24 hours by itself without sanding
Lower temperature or film thickness higher than 70µm will extend drying times	

## TECHNICAL DATA

Based on ready-for-use mixed paint including thinner:	
VOC (g/L):	392-568 g/L (depending on colour and dilution)
Solid content (weight):	45-64 %
Solid content (volume):	35-55 %
Solvent content (weight):	36-55 %
Specific gravity (Ready for use)	1.04-1.13 Kg/L
Theoretical coverage:	5.8-9.1 m <sup>2</sup> /L at 60 microns DFT
Gloss:	High Gloss

## PRODUCT CODES AND DESCRIPTIONS

Selemix Code	Short Code	Product Description	Packsize	
1.775.5000/E15K	7-550	Polyurethane UHS	15	Kg
1.991.5075/E5	9-075	Direct HS Hardener	5	Lt
1.991.1480/E5	1-480	Direct PUR Thinner	5	Lt
1.991.1470/E5	1-470	Slow Direct Thinner	5	Lt

## HEALTH AND SAFETY

For comprehensive Health, Safety and Environmental advice, please refer to the relevant Material Safety Data Sheets and Product can labels.

## THIS PRODUCT IS FOR PROFESSIONAL USE ONLY

The information given in this sheet is for guidance only. Any person using the product without first making further enquiries as to the stability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of our experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.

### FOR FURTHER INFORMATION PLEASE CONTACT:

Selemix Customer Service and Sales Group  
Needham Road  
Stowmarket, Suffolk  
IP14 2AD, England  
Tel: 01449 771771