

PRODUCT DATA SHEET

Sikafloor®-29 PurCem®

HIGH STRENGTH POLYURETHANE COVING AND DETAILING MORTAR

PRODUCT DESCRIPTION

Sikafloor®-29 PurCem® is a multi-component, polyurethane hybrid mortar. It has high impact and mechanical resistance, good resistance against chemicals and wear. It is typically installed at 3 -9 mm thickness.

USES

Sikafloor®-29 PurCem® may only be used by experienced professionals.

Sikafloor® -29 PurCem® is used as a coving mortar, detailing and vertical rendering with Sikafloor® PurCem® floor systems.

CHARACTERISTICS / ADVANTAGES

- Good wear resistance
- High mechanical and impact resistance
- High softening point
- Good chemical resistance
- Non tainting /odourless
- Fast curing
- VOC free and environmental friendly
- Can be applied to substrates with high moisture content (7 days old or mature damp concrete)

ENVIRONMENTAL INFORMATION

LEED Rating:

USGBC LEED® Rating. Confirms Section FQ (Indoor Environment Quality), Credit 4.2 Low Emitting Materials Paints and Coatings (VOC content ≤ 50 g/l).

APPROVALS / STANDARDS

- Polyurethane screed for concrete protection according to the requirements of EN 1504-2:2004 and conforms to the requirements of EN 13813: 2002, DoP 02 08 02 02 003 0 000001 1088, certified by Factory Production Control Body, 0086, certificate 541325, and provided with the CE-mark.
- EN1186, EN 13130, and prCEN/TS 14234 standards, and the Decree on Consumer Goods, representing the conversion of directives 89/109/EEC, 90/128/EEC and 2002/72/EC for contact with food stuffs, according to test report by ISEGA, 32758 U11 and 32759 U11, both dated December 6th, 2011. (Tests performed on Sikafloor® -20/21/22/29 and 31 PurCem® in standard and LP versions).
- British Standards Specifications (BSS) acceptance for use in the UK. Campden and Chorleywood Food Research Association, Ref. S/REP/125424/1a and 2a, dated 8th February, 2012
- Fire classification report according to EN 13501-1 from Exova Warrington Fire for Sikafloor®-31 PurCem® No.31050, dated 24th of March, 2012
- Liquid water transmission rate test report from the Technology Centre, Ref. 15456 dated January 25th, 2012
- Impact resistance values tested at PRA, Ref. nº 75221-151, dated January 11th, 2012

PRODUCT INFORMATION

Chemical Base	Water-based polyurethane cement hybrid	
Packaging	Part A	1.50 kg plastic drum
	Part B	1.50 kg plastic jerrycan
	Part C	19.0 kg plastic bags
	Part A+B+C	22.0 kg ready to mix units
Appearance / Colour	Part A	coloured liquid
	Part B	brown liquid
	Part C	natural grey powder
Shelf Life	Part A	12 months from date of production. Protect from freezing.
	Part B	12 months from date of production. Protect from freezing.
	Part C	6 months from date of production. Must be protected from humidity.
Storage Conditions	The package must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.	
Density	Part A+B+C mixed: ~ 1.97 kg/l ± 0.03 (at +20°C)	

TECHNICAL INFORMATION

Shore Hardness	Shore D: 80 - 85	(ASTM D 2240)
Compressive Strength	> 44 N/mm ² after 28 days at +23°C / 50% r.h.	(BS EN 13892-2)
Flexural Strength	> 8 N/mm ² after 28 days at +23°C / 50% r.h.	(BS EN 13892-2)
Tensile Adhesion Strength	concrete failure	(EN 1542)

SYSTEM INFORMATION

Systems	As a coving mortar and render mortar in Sikafloor® PurCem® applications.
---------	--

APPLICATION INFORMATION

Mixing Ratio	Part A : B : C = 1 : 1 : 11.7 (packaging size = 1.5 : 1.5 : 19) by weight. Mix full units only.
Ambient Air Temperature	+10°C min. / +40°C max.
Consumption	~ 2.0 kg/m ² /mm
Layer Thickness	3 – 9 mm
Relative Air Humidity	85% max.
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.
Substrate Temperature	+10°C min. / +40°C
Substrate Moisture Content	Can be installed on substrates with higher moisture content. No ponding water. Check rising moisture. The substrate needs to be visibly dry and have adequate pull-off strength min 1.5 N/mm ² .

Pot Life

Temperatures	Time
+10°C	~ 35 - 40 minutes
+20°C	~ 22 - 25 minutes
+30°C	~ 15 - 18 minutes
+35°C	~ 12 - 15 minutes

Curing Time

Before overcoating Sikafloor®-29 PurCem® allow:

Substrate temperature	Minimum	Maximum
+10°C	20 hours	72 hours
+20°C	10 hours	48 hours
+30°C	5 hours	24 hours
+35°C	5 hours	24 hours

Times are approximate and will be affected by changing ambient and substrate conditions, particularly temperature and relative humidity.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull of strength shall not be less than 1.5 N/mm². If in doubt apply a test area first.

MIXING

Premix part A with a low speed electric stirrer and then add part B and mix for 30 seconds. Make sure all pigment is uniformly distributed. Use a double paddle (axis) mixer and gradually add 1 part C (aggregate) to the mixed resin. **DON'T DUMP!**

For the colourpack version, premix 1 part A neutral with a low speed electric stirrer and add 1 part D to it. Mix until a uniform colour is achieved. Add 1 part B and mix for 30 seconds. Make sure all pigment is uniformly distributed. Use a double paddle (axis) mixer and gradually add 2 part C (aggregate) to the mixed resin. **DON'T DUMP!**

Allow part C to blend for further 2 minutes minimum, to ensure complete mixing and a uniform moist mix is obtained. During the operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once (parts A+B+C) to ensure complete mixing. Mix full units only.

Mixing tools:

Use a low speed electric stirrer (300-400 rpm) for mixing parts A and B. For preparation of the mortar mix use a pan type revolving mixer.

APPLICATION

Apply the mixed Sikafloor®-29 PurCem® onto the ready primed substrate and compact to the appropriate thickness, then finish the detailing profile with a coving trowel or steel float. Apply Sikafloor®-29 PurCem® while the primer is still tacky. If the primer becomes tack free, reapply the primer.

CLEANING OF TOOLS

Clean all tools and application equipment with Thinner

C immediately after use. Hardened/cured Sikafloor®-29 PurCem® can only be mechanically removed.

FURTHER DOCUMENTS

Please refer to:

- Sika® Information Manual Mixing and Application of Flooring Systems
- Sika® Information Manual Surface Evaluation & Preparation
- Sikafloor® PurCem® System Data Sheets

LIMITATIONS

Do not apply to PCC (polymer modified cement mortars) that may expand due to moisture when sealed with an impervious resin.

Always ensure good ventilation when using Sikafloor®-29 PurCem® in a confined space, to prevent excessive ambient humidity.

Freshly applied Sikafloor®-29 PurCem®, must be protected from damp, condensation and direct water contact (rain) for at least 24 hours.

Protect the substrate during application from condensation from pipes or any overhead leaks.

Do not apply to cracked or unsound substrates.

Always allow a minimum of 48 hours after product application prior to placing into service in proximity with food stuffs.

Products of the Sikafloor®-PurCem® product range are subject to discolouration when exposed to UV radiation. Extend depends on colour. There are no measurable losses of any properties when this occurs and it is a purely aesthetical matter. Products can be used outside provided the change in appearance is acceptable by the customer.

In some slow curing conditions, soiling of the surface may occur when opened to foot traffic, even though mechanical properties have been achieved. It is advised to remove dirt using a dry mop or cloth. Avoid scrubbing with water for the first three days.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC Product category IIA / j type wb) is 140 g/l (Limit 2010), for the ready to use product. Sikafloor®-29 PurCem, is VOC free for the ready to use product.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet

Sikafloor®-29 PurCem®
February 2020, Version 01.02
020814020020000022

Sikafloor-29PurCem-en-GB-(02-2020)-1-2.pdf