

TECHNICAL DATA SHEET

TRAWLAK FISHROOM PRESERVATIVE

TDS: TMV6041
541/V604/1

DESCRIPTION:

Teamac Trawlak Fishroom Preservative is a Shellac based, traditional coating for the fishing industry. Its incredibly quick drying formulation seals wood with an attractive, hard amber finish. Knot resistant formulation seals in stains.

RECOMMENDED USE:

Teamac Trawlak Fishroom Preservative is suitable for all types of wood and steel. It can be used on walls of trawler fish rooms, wooden fish crates and pallets. When applied coat on coat, quickly dries to a hard gloss finish.

AVAILABILITY:

5 litre

FINISH:

Gloss

COLOUR:

Translucent Brown

TYPICAL S.G. (SPECIFIC GRAVITY):

0.89 @ 20 °C

VOLUME SOLIDS:

32%

WET FILM THICKNESS W.F.T

72 microns

DRY FILM THICKNESS D.F.T

23 microns

EXPECTED SPREADING RATE:

14 sq.m / litre
@ 23 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

29 sec. B4 cup @ 25 °C

FLASH POINT:

16 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 10 mins @ 20 °C

Hard dry: 3 hours @ 20 °C

Full hardness: 24 hours @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

3 hours

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

544 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush

Thinner Thinners 6 (10%)
(Max vol):

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning Thinner 6
solvent:

Recoat 3 hours
interval:

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminants.

MIXING INSTRUCTIONS:

Stir well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

N/A

SUBSEQUENT COAT:

Teamac Trawlak Fishroom Preservative.

REMARKS:

N/A

HEALTH AND SAFETY:

See safety data sheet - SDS 10732

ISSUED:

15 April 2014

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 320194.

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMAC
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: info@teamac.co.uk
www.teamac.co.uk