

TECHNICAL DATA SHEET

TDS: CVG15065B

BRICK AND TILE PAINT GLOSS RED

348/G150

DESCRIPTION:

Coo-Var Brick and Tile Paint Gloss Red is an alkyd based versatile gloss red finish.

RECOMMENDED USE:

Coo-Var Brick and Tile Paint Gloss Red is ideal for use on porches, front walls, out buildings, most brickwork, masonry or stone.

AVAILABILITY:

0.5 litre, 1 litre, 2.5 litre, 5 litre

FINISH:

Gloss

COLOUR:

Red

TYPICAL S.G. (SPECIFIC GRAVITY):

1.16 @ 20 °C

VOLUME SOLIDS:

49%

WET FILM THICKNESS W.F.T

75 microns

DRY FILM THICKNESS D.F.T

35 to 40 microns

EXPECTED SPREADING RATE:

13 sq.m / litre

@ 40 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

4.5 Poise @ 25 °C

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 5 hours @ 20 °C

Hard dry: 24 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours or overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

399 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or roller Airless Spray

Thinner Thinners 14 Thinners 14
(Max vol): (10%) (10%)

Nozzle size: 0.011" - 0.013"

Nozzle 1800 to 2000 psi
pressure:

Cleaning Thinners 14
solvent:

Recoat 12 hours or
interval: overnight

SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminants.

Use Coo-Var Masonry Stabiliser on unstable brick, screed or plaster prior to painting.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: info@coo-var.co.uk

www.coo-var.co.uk

Existing painted surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose, flaking material and treat bare areas as new substrate then prepare accordingly.

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. Care must be taken during application that the temperature is above the dew point to avoid any contamination. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Apply Direct to stable surfaces (see Surface Prep section)

SUBSEQUENT COAT:

Coo-Var Brick and Tile Paint Gloss Red

REMARKS:

HEALTH AND SAFETY:

See safety data sheet - SDS 10582

ISSUED:

12 May 2011

REVISION:

0

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR
Email: info@coo-var.co.uk
www.coo-var.co.uk