

SIGMACOVER™ 690 LT

(SIGMACOVER™ 690 WG)

DESCRIPTION

Two-component, high solids aluminum pigmented polyamine cured modified epoxy primer/coating for temperatures of 0°C (32°F) up to 10°C (50°F)

PRINCIPAL CHARACTERISTICS

- Good curing at temperatures down to 0°C (32°F)
- Primer/coating designed for maintenance
- Low VOC
- Good flow properties
- Self priming coating tolerant to lower grades of steel preparation
- Compatible with most aged, good adhering coatings
- Good recoatability with epoxy and polyurethane paints
- Good abrasion resistance
- For substrate temperatures above 10°C (50°F), the standard SIGMACOVER 690 (7414) shall be used

COLOR AND GLOSS LEVEL

- Aluminum light and dark
- Semi-gloss

BASIC DATA AT 10°C (50°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (10.8 lb/US gal)
Volume solids	88 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 167.0 g/kg UK PG 6/23(92) Appendix 3: max. 222.0 g/l (approx. 1.9 lb/US gal)
Recommended dry film thickness	75 - 125 µm (3.0 - 5.0 mils) depending on system
Theoretical spreading rate	11.7 m²/l for 75 µm (471 ft²/US gal for 3.0 mils) 7.0 m²/l for 125 µm (282 ft²/US gal for 5.0 mils)
Dry to touch	5 hours
Overcoating Interval	Minimum: 24 hours Maximum: 4 months
Full cure after	5 days
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

SIGMACOVER™ 690 LT

(SIGMACOVER™ 690 WG)

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Atmospheric exposure conditions

- Steel; power tool cleaned to ISO-St2 or blast cleaned to ISO-Sa2 for good corrosion protection
- Steel with approved shop primer; sweep blasted to SPSS-Ss or power tool cleaned to SPSS-Pt2
- Existing sound coating systems; sufficiently roughened, dry and cleaned

Immersion in water

- Steel; blast cleaned to ISO-Sa2½
- Steel with approved shop primer; sweep blasted to SPSS-Ss or power tool cleaned to SPSS-Pt3

Substrate temperature

- DONOTUSE Above 5°C (41°F), and at least 3°C (5°F) above dew point

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 77.5:22:5

- Use wintergrade hardener
- The temperature of the mixed base and hardener should be above 10°C (50°F), otherwise extra thinner may be required to obtain application viscosity
- Thinner should be added after mixing the components
- Adding too much thinner results in reduced sag resistance and slower cure

Pot life

3 hours at 10°C (50°F)

Note: See ADDITIONAL DATA – Pot life

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.8 – 2.0 mm (approx. 0.070 – 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)



SIGMACOVER™ 690 LT

(SIGMACOVER™ 690 WG)

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 5%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.48 – 0.53 mm (0.019 – 0.021 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 5%

Cleaning solvent

THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
75 µm (3.0 mils)	11.7 m ² /l (471 ft ² /US gal)
100 µm (4.0 mils)	8.8 m ² /l (353 ft ² /US gal)
125 µm (5.0 mils)	7.0 m ² /l (282 ft ² /US gal)

Overcoating interval for DFT up to 125 µm (5.0 mils)					
Overcoating with...	Interval	0°C (32°F)	5°C (41°F)	10°C (50°F)	15°C (59°F)
itself	Minimum	64 hours	36 hours	24 hours	20 hours
	Maximum	5 months	5 months	4 months	3 months

Notes:

- Surface should be dry and free from any contamination
- For polyurethane paints the minimum overcoating time should be raised with 50%

SIGMACOVER™ 690 LT

(SIGMACOVER™ 690 WG)

Curing time for DFT up to 125 µm (5.0 mils)

Substrate temperature	Dry to touch	Dry to handle	Full cure
0°C (32°F)	18 hours	26 hours	14 days
5°C (41°F)	12 hours	20 hours	10 days
10°C (50°F)	5 hours	16 hours	7 days
15°C (59°F)	4 hours	12 hours	6 days

Note: Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

Pot life (at application viscosity)

Mixed product temperature	Pot life
5°C (41°F)	4 hours
10°C (50°F)	3 hours

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490



SIGMACOVER™ 690 LT

(SIGMACOVER™ 690 WG)

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

