

Mon 10/10/2022

The PTV (pendulum test) refers to the static and dynamic coefficient of friction (coF) or degree of non-slip as per ASTM D1894.

Please see values for our products below:

Product	Average Static coF (dry)	Average Dynamic coF (dry)	Average Static coF (wet)	Average Dynamic coF (wet)
Protectakote textured	0.78	0.72	0.60	0.53
Protectakote UVR textured	0.67	0.60	0.57	0.45
Safekote	0.51	0.39	0.42	0.26
Protectakote WB	1.09	0.93	0.89	0.86
Safekote WB	0.88	0.61	0.68	0.58

Hannah Lewis
Formbar Limited

The Cart Shed, Manor Farm Courtyard, West Hagbourne, Oxfordshire, OX11 0ND

Tel: +44 (0)1235 850368

www.formbar.co.uk



We take our responsibilities to GDPR seriously and if you would like to see our privacy policy then do email to request it. If you would like us to remove your contact details from our records please replay to this email requesting the removal of all your information from our system.

The information in this e-mail and any files transmitted with it, is intended only for the named recipient(s) or entity and may be privileged or confidential. If you are not the intended recipient, please notify us immediately and do not copy, distribute or take any action based on its contents. This e-mail is not intended to constitute a commitment or an offer to enter into a contract by Formbar Limited.

Formbar Limited (05155971 England), Registered Office: 133 Kynaston Road, Didcot, OX11 8HB
VAT No GB 866 5550 89