

Testing in accordance with ISO 12944-6 (2018)

Corrosivity Category C5 Low

Macropoxy 400 at 125µm

Acrolon 7300 at 55µm

Customer : Sherwin-Williams Co.
PO Box 94785
Cleveland, OH 44101
United States

Customer Reference : 427573

Element Project Ref. : ERO027446P

Report Number : ERO027446-5_C5L

Author : J.J. Rokx

Date Report : 08-11-2018

Number of Pages : 13

Distribution : Sherwin-Williams Co.

Attn. Mr. D. Fielding 1x

Files Element Materials Technology Amsterdam 1x

© Copyright:

Element Materials Technology Amsterdam B.V.

All rights reserved. Nothing of this publication may be multiplied, stored in an automatic databank, or made public in any form or in any way, either electronically, mechanically, by photocopy, recordings, or any other way without preceding written permission of Element Materials Technology

Unless otherwise expressly agreed with us in writing, all our supplies are exclusively subject to our Terms of delivery and all work is exclusively carried out by us subject to the stipulations concerning the Execution of Works as filed at the Chamber of Commerce at Amsterdam on June 27, 2005 under no. 33194077



1. Introduction

Sherwin-Williams requested Element Materials Technology Amsterdam to perform coating testing on a multi coat scheme of Macropoxy 400 at 125µm and Acrolon 7300 at 55 µm DFT in accordance with ISO 12944-6 (2018), "Paints and varnishes – Corrosion protection of steel structures by protective paint systems – Part 6: Laboratory performance test methods".

Surface preparation and application were carried out in an industrial paint application facility rather than controlled laboratory conditions.

Samples were supplied by Sherwin-Williams in accordance with the requirements listed within ISO 12944-6 (2018), "Paints and varnishes – Corrosion protection of steel structures by protective paint systems – Part 6: Laboratory performance test methods"


Corrosivity category as defined in ISO 12944-2 (2017), "Paints and varnishes – Corrosion protection of steel structures by protective paint systems -- Part 2: Classification of environments"

Testing was performed between the 26th September 2018 and the 23rd October 2018 at Element facilities in Amsterdam

2. Summary

**The coating system is in full accordance with the requirements of ISO 12944-6 (2018),
Corrosivity Category C5 Low.**

Author: J.J. Rokx
Coating consultant



Authorised by: M. Halliday
Global coating specialist

