

Sika Limited
Miller Street
PR1 1EA Preston
UNITED KINGDOM

Eurofins Product Testing A/S
Smedeskovvej 38
DK-8464 Galten
Denmark

Tel. +45 70 22 42 76
Fax +45 70 22 42 75
eurofins@eurofins.dk
www.eurofins.com/product-emissions

Date
06 October 2015

Our ref.
392-2015-00292201

Test Report – ISO 11890-2 / ASTM D6886

Sample material

Sample identification	Sikagard 403W		
Product type	Water based paint		
Batch No.	3001508234		
Production date	08/06/15		
Product data	Density: 1.340 g/ml		(Information from client)
Date received	24/09/2015		
Analytical period	24/09/2015 – 06/10/2015		

Methods applied

Method	Principle	Parameter	Reporting limit	Uncertainty (U _m)
EU Directive 42/2004/EC ISO 11890-2 (2013) ASTM D6886-12	GC/MS and GC/FID	Content of volatile and semi-volatile organic compounds (VOC/SVOC) in paints and varnishes	1 g/l	20 %
<p>Volatile Organic Compounds (VOC) include all organic compounds with an initial boiling point less than or equal to 250°C measured at standard pressure of 101,3 kPa.</p> <p>Semi-Volatile Organic compounds (SVOC) include any organic compounds with an initial boiling point greater than 250°C and less than 370 °C measured at standard pressure of 101,3 kPa.</p> <p>VOC content and SVOC content are determined in conformity with ISO 11890-2 standard, CEPE Guidance document referenced CEPE/EC/2015-04-13, and the Commission Decision 2014/312/EU of 28 May 2014 establishing the ecological criteria for the award of the EU Ecolabel for indoor and outdoor paints and varnishes by considering its most recent amendments and its most recent User Manual.</p> <p>Analyses are performed with a slightly polar gas chromatographic column (HP-5) system, using <i>n</i>-tetradecane (C₁₄H₃₀) and <i>n</i>-docosane (C₂₂H₄₆) as marker compounds for the SVOC determination. Mass spectrometric detector is used for VOCs and SVOCs' identification and flame ionization detector is used for quantification.</p> <p>Identified SVOCs and VOCs are quantified with their authentic response factors, or with their relative response factors using 1,2-diethoxyethane as internal standard.</p> <p>Remaining unknown SVOC and VOC peaks are quantified in diethyl adipate equivalents.</p>				

*)Not accredited

The expanded uncertainty U_m equals 2 x RSD%

The test results relate only to the items tested.

The report shall not be reproduced except in full without the written approval of the testing laboratory.

Analytical results

392-2015-00292201	CAS	Content, g/l
Total VOC	-	< 1
Unidentified *	-	1.6
Total SVOC	-	1.6

Eurofins Product Testing A/S

Nikolaj Røjkjær Andersen
Analytical Chemist

*)Not accredited

The expanded uncertainty U_m equals 2 x RSD%

The test results relate only to the items tested.

The report shall not be reproduced except in full without the written approval of the testing laboratory.