ZINGALUFER

Zingalufer is a one-component Micaceous Iron Oxide moisture curing polyurethane sealer that can be used over Zinga and AquaZinga.

It has excellent resistance to both salts and chemical exposure and can be used as an intermediate layer or as a topcoat in covered areas where there is no UV exposure.

Zingalufer can be used on many structures in both atmospheric and immersed situations and can extend the service-life of many coating systems.

On structures such as sewage tanks it can be applied by airless spray at film-builds of 200μ m DFT. Where it is used as a sealer beneath coatings such as two component acrylics, it can be applied with a conventional spray gun at film-builds in the range of 40 - 60 μ m DFT.

Full product specification sheets are available to download at **www.zinga-uk.com** or from our office on **01243 770 726**.

On Zinganised cast-iron or cast steel keels on GRP yachts for example, it can be applied (undiluted) by short-nap rollers and so makes for an easy application on site.

ZINGALUFER

- Resistant to chemicals.
- Resistant to abrasion.

at 80µm DFT

- Dirt repellent.
- \bullet Suitable for covering vertical surfaces to 200 μm in one coat.
- Available in 1L or 4L tins.
- Grey colour.

Theoretical Coverage

At a thickness of: 80 μ m DFT - 7.5 m²/Lt.

