

TIMBERCOAT INTUMESCENT 30/60 BASECOAT

Fire Protection Upgrade Systems for bare & suitable multi-layer painted wood and wood derivatives

Key Benefits:

Part 1 of system achieve 30 or 60 minute Fire Resistance for compartmentation
Finished system forms a smooth aesthetically pleasing, durable finish resistant to repeated cleaning to internal and external wood.

Achieves EN Class B s1 d0

Exceptional adhesion
Permanent protection
Tintable to undercoat shades
Water-based

How it works: In the event of a fire it expands, forming a heat-resistant char to insulate the surface
Overcoated with Thermoguard Safewood or Anti-Microbial SFR Smoke & Flame Retardant

Pack Sizes *5kg & 20 kg cans for 30 & 60 mins protection on wood and wood derivative boards*

Coverage Follow on-can guide to coverage, do not overspread as this compromises the system and results in non-compliance and inability to certify.

Drying Times In normal conditions touch dry one hour
Overpaintable with Safewood SFR or Dualcoat SFR after 4 hours.

Application Min 8°C max 30°C.
Conditions Max relative Humidity 75%.
Surface should be at least 3°C above the dew point, free from condensation

Typical Use First part of a system for use as an intumescent basecoat

VOC Content Low Voc. Limit for this product (cat A/i) is 140 g/l. This product contains just 16 g/lv

Composition Catalytic powder, expansion agent, char former, char hardeners & fibres Binder:
Fire protection adhesive grade rapid reaction acrylic resin. Water based

TIMBERCOAT INTUMESCENT 30/60 BASECOAT

Preparation	All surfaces must be clean and dry. Remove all possible surface contaminants such as grease, smoke residues, silicates etc. Seal water-stain risks with stain blocking sealer suitable to overcoat with water-based acrylic paints Abrade hard or smooth surfaces with wetted 120 grit wet-or dry abrasive or dust extracting abradar. Rinse off slurry while still damp. When dry, remove any loose or suspect material back to firm edge. Fill and repair any damage to the substrate using a good quality remedial filler
Application	Apply at rate stated on can to protect surfaces & enable project Certification
Brush & Roller	Woven fabric roller sleeves and synthetic bristle brushes
Spray	Pressure Pot & Gun conventional unit with small compressor: Ensure all traces of solvent flushed out Thin 5 > 10% with water to spray viscosity. Adjust fluid flow & air flow as normal for acrylic emulsion paint OR Airless Graco 1500, 3500 or equivalent. 3/8" line, 30 mesh filter on machine, no filter in gun. 521 or 523, broad areas 621 or 623 tip Ensure coverage is applied as per can i.e., 25 sqm can covers 25 sqm
Certification	Once the works are complete the relevant certification can be applied for via the Thermoguard website. Please state any specification number to assist
Test Data	FIRE TEST STANDARDS in UKAS and EOTA accredited Fire Test laboratory BS EN Class B s1 d0 Compliant for Class 0, plus full smoke protection For 30 or 60 mins contact Technical 01142 768008 (2) technical@thermoguard.co.uk
Cleaning	Return as much unused material to its original container as possible. Wash brushes rollers and guns with clean waters immediately following use.
Health And Safety	Please refer to the relevant Safety Data Sheet for full details of this product Apply all products in accordance with BS 6150:2019- Code of practice for painting of buildings. Do not store this product in cold temperatures below 5°C or above 30°C.
Further Support	If you require any further assistance, please contact Thermoguard Technical Helpdesk on 01142 768008 option 2 or email technical@thermoguard.co.uk