

## TECHNICAL DATA SHEET

TDS: CVV60136

### MASONRY STABILISER

340/V601/36

#### DESCRIPTION:

Coo-Var Masonry Stabiliser is a binding and sealing solution for degraded and porous masonry.

#### RECOMMENDED USE:

Coo-Var Masonry Stabiliser is designed for use on unstable brick, screed or plaster prior to painting.

#### AVAILABILITY:

1 litre, 2.5 litre, 5 litre

#### FINISH:

N/A

#### COLOUR:

Clear

#### TYPICAL S.G. (SPECIFIC GRAVITY):

0.96 @ 20 °C

#### VOLUME SOLIDS:

28%

#### WET FILM THICKNESS W.F.T

110 microns

#### DRY FILM THICKNESS D.F.T

25 to 30 microns

#### EXPECTED SPREADING RATE:

9 sq.m / litre

@ 110 microns D.F.T

Coverage dependant on the porosity of the surface.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

#### TYPICAL VISCOSITY:

20 sec. B4 cup @ 25 °C

#### FLASH POINT:

Above 32 °C (closed cup)

#### DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 2 hours @ 20 °C

Hard dry: 12 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

#### MINIMUM OVERCOATING TIME:

12 hours or overnight

#### APPLICATION SPECIAL CONDITIONS:

N/A

#### VOC CONTENT:

571 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

#### APPLICATION DETAILS:

Application N/A  
restrictions

Method: Brush or Roller

Thinner Thinners 14  
(Max vol): (10%)

Nozzle size: N/A

Nozzle N/A  
pressure:

Cleaning Thinners 14  
solvent:

Recoat 12 hours or  
interval: overnight

#### SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminates.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

**MASONRY STABILISER****340/V601/36**

---

Remove all loose, flaking material.

**MIXING INSTRUCTIONS:**

Mix well before use.

**APPLICATION CONDITIONS:**

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

**PRECEDING COAT:**

None - Apply direct to surface.

**SUBSEQUENT COAT:**

Suitable topcoat - check compatibility first.

**REMARKS:****HEALTH AND SAFETY:**

See safety data sheet - SDS 10766

**ISSUED:**

23 May 2012

**REVISION:**

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

---

**Ellenshaw Works**

**Lockwood Street, Hull HU2 0HN**

**Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266**

**COO-VAR**

**Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)**

**[www.coo-var.co.uk](http://www.coo-var.co.uk)**