

TECHNICAL DATA SHEET

TDS: CVQ462
207/Q462

SEALER COAT FOR GP101

DESCRIPTION:

Sealer Coat for GP101 is likely to be required before applying GP101 Graffiti Protection System over porous surfaces. A transparent sealer that also offers excellent water and mildew resistance. Low odour.

RECOMMENDED USE:

Sealer Coat for GP101 can also be used to minimise darkening of sandstone and other natural stone.

AVAILABILITY:

2.5 litre

FINISH:

Off Gloss

COLOUR:

Clear

TYPICAL S.G. (SPECIFIC GRAVITY):

0.98 to 1.02 @ 20 °C

VOLUME SOLIDS:

WET FILM THICKNESS W.F.T

65 microns

DRY FILM THICKNESS D.F.T

22 microns

EXPECTED SPREADING RATE:

10 to 15 sq.m / litre

@ 22 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

18 to 24 sec. B4 cup @ 25 °C

FLASH POINT:

Non-flammable

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 1.5 hours @ 20 °C

Hard dry: 6 hours @ 20 °C

Full hardness:

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

2 Hours Itself / 24 Hours GP101

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

<30 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application Do not apply below 7 °C. restrictions

Method: Brush or Roller

Thinner Clean Water
(Max vol):

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning Clean Water
solvent:

Recoat 2 Hours Itself /
interval: 24 Hours GP101

SURFACE PREPARATION:

All surfaces should be clean, dry and free from oil, grease and loose flaking material.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

SEALER COAT FOR GP101**207/Q462**

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice.
Do not apply if the temperature is likely to drop below 7 °C during application or during the drying process.

PRECEDING COAT:

N/A

SUBSEQUENT COAT:

Sealer Coat for GP101 or GP101 Graffiti Protection System

REMARKS:**HEALTH AND SAFETY:**

See safety data sheet - SDS 11192

ISSUED:

20 October 2017

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-var
Email: info@coo-var.co.uk
www.coo-var.co.uk