



# FASTRAC GP ANTICORROSIVE PRIMER AP70

**A fast drying modified alkyd anticorrosive primer.**

## Recommended Areas of Use

Intended for use as a general use fast drying prefabrication or system primer on properly prepared ferrous surfaces.

## Certificates & Approvals

Manufactured under the auspices of an ISO 9001:2008 quality & ISO 14001:2004 environmental management systems.

## Properties

<b>Gloss</b>	Matt (<10%)	<b>Surface dry</b>	1 hour
<b>Theoretical Coverage</b>	9 m <sup>2</sup> /L/coat	<b>Minimum overcoating time</b>	16 hours minimum
<b>Recommended number of coats</b>	1 or 2 full coats	<b>Maximum overcoating time</b>	Unlimited
<b>Density</b>	1.59 kg/L	<b>Minimum application conditions</b>	Down to 5 °C & 60% RH maximum (but must be 3 °C above dew point)
<b>Volume solids</b>	60%	<b>Full cure</b>	7 days
<b>Flash point (Abel closed cup)</b>	26 °C		
<b>VOC</b>	320 g/L	<b>Shelf life</b>	12 months minimum in original unopened containers.
<b>Thinner / Cleaning</b>	Bradite Thinner TW35	<b>Colour range</b>	Dark Grey & Red Oxide
<b>Recommended wet film thickness</b>	58 microns/coat	<b>Recommended dry film thickness</b>	35 microns/coat

## Suitable Surfaces

Ferrous surfaces blast cleaned to SIS Sa 2<sup>1/2</sup> minimum or mechanically prepared to SIS St 3 minimum. Suitable for coating over compatible coatings which are clean, dry and abraded.

## Application Information

Application and use should always conform to the codes of practice described in BS 6150 and BS 5493.

**Brush and Roller** – supplied ready for use. Thin with 0 - 5% Bradite Thinner TW35 if required.

**Conventional Air Spraying** - Thin with 10 - 20% Bradite Thinner TW35 as required, tip size - 2.0mm, tip pressure 60psi (0.4MPa) approximately.

**Airless Spraying** - Thin with 0 - 15% Bradite Thinner TW35 as required, tip size - 19 thou (0.48mm) approximately, tip pressure - 2100 psi (15MPa) approximately.

## Cleaning

Clean all equipment immediately after use with Bradite Thinner TW35 for best results.

## Preparation

High pressure steam cleaning to remove all loose, flaking paint and contamination back to a sound surface. Bradite TD39 industrial strength detergent, washing and rinsing should be used with scrubbing to remove grease or oil.

Remove all rust scale, loose mill scale or other corrosion products by scraping and mechanical cleaning to SIS-St 3 (ISO 8501-1:1998).

Intact areas of existing coatings should be roughened by abrasive manual or disc sanding, feathering back to a sound coating edge. Cracks and pits should be filled using a suitable metal filler before painting. Substrate should be dust free and completely dry before coating.

## Notes

Light surface rusting may be effectively treated using one coat of Bradite FASTRAC Rust Converter RC46 prior to application of Bradite FASTRAC GP Anticorrosive Primer AP70.

New galvanised steel should be thoroughly degreased and then pre-treated with Bradite Mordent Solution TM38 prior to application of Bradite FASTRAC GP Anticorrosive Primer AP70. Alternatively, or for other non-ferrous metals, prime with Bradite Barrier Primer EU96 before application of selected Bradite finish.

Suitable for use under many Bradite finishes such as Fastrac Gloss ME53 & Fastrac Satin SE53.

## Summary Safety Information

Always refer to the Health and Safety sheet for the product before use and observe the warning phrases on the label.

**Disclaimer** - The information on this data sheet is correct to the best of our knowledge and experience. Bradite reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, nor does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.