



HB MIO BUILD FINISH COAT_{AM60}

A high build high performance single pack modified alkyd micaceous iron oxide intermediate coat or finish.

Recommended Areas of Use

Perfect for the protection and decoration of ferrous & non-ferrous metals either as an intermediate build coat or finish.

Certificates & Approvals

Manufactured under the auspices of an ISO 9001:2008 quality & ISO 14001:2004 environmental management systems.

Properties

Gloss	Eggshell (approx. 20%)	Surface dry	4 hours
Theoretical Coverage	12 m ² /L/coat	Minimum overcoating time	16 hours minimum
Recommended number of coats	1 to 2 full coats	Maximum overcoating time	Unlimited
Density	1.66 kg/L	Minimum application conditions	Down to 10 °C (but must be 3 °C above dew point)
Volume solids	48%	Full cure	7 days
Flash point (Abel closed cup)	38 °C	Shelf life	12 months minimum in original unopened containers.
VOC	411 g/L	Colour range	Metallic, limited range (see below)
Thinner / Cleaning	Bradite Thinner TW35	Heat Resistance	90 °C dry heat (some discolouration may occur)
Recommended wet film thickness	100 microns/coat	Recommended dry film thickness	48 microns/coat

Suitable Surfaces

For all suitably primed ferrous & non-ferrous metals which are dry, free of contamination, dust and have been properly prepared and/or primed. Compatibility with existing coatings should be confirmed by preparing and painting a test area.

Application Information

Application and use should always conform to the codes of practice described in BS 6150 and BS 5493. Best results are obtained by spraying.

Brush and Roller – supplied ready for use. Use natural bristle brush, tapered and flagged, for best appearance. Thin, if required, with 0 - 5% Bradite Thinner TW35. Keep application in one direction to avoid “suede” like appearance & colour discontinuity.

Conventional Air Spraying - Thin with 5 - 15% Bradite Thinner TW35 as required, tip size – 3 mm, tip pressure 60psi (0.4MPa) approximately.

Airless Spraying - Thin with 0 - 10% Bradite Thinner TW35 as required, tip size - 18 thou (0.46mm) approximately, tip pressure - 2100 psi (15MPa) approximately.

Cleaning

Clean all equipment immediately after use with Bradite Thinner TW35 for best results.

Preparation

High pressure steam cleaning to remove all loose, flaking paint and contamination back to a sound surface. Bradite TD39 industrial strength detergent, washing and rinsing should be used with scrubbing to remove grease or oil.

Remove all rust scale, loose mill scale or other corrosion products by scraping and mechanical cleaning to SIS-St 3 (ISO 8501-1:1998).

Intact areas of existing coatings should be roughened by abrasive manual or disc sanding, feathering back to a sound coating edge. Cracks and pits should be filled using a suitable metal filler before painting. Substrate should be dust free and completely dry before coating.

Notes

Light surface rusting may be effectively treated using one coat of Bradite Rust Converter RC46 prior to application of this product.

New galvanised steel should be thoroughly degreased and then pre-treated with Bradite Mordent Solution TM38 prior to application of this product. Alternatively, or for other non-ferrous metals, prime with Bradite Barrier Primer EU96 before application of this product.

For the protection of metal structures subject to more demanding exposure scenarios, application of Fastrac Antico Primer AP71 or SORTED WP45, prior to finishing with this product, is highly recommended.

Summary Safety Information

Always refer to the Health and Safety sheet for the product before use, and observe the warning phrases on the label.

Disclaimer - The information on this data sheet is correct to the best of our knowledge and experience. Bradite reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, nor does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.