

Acothane Twin Pack Repair Kit

Product Description	A solvent free, two pack polyurethane mastic repair kit for the repair of small defects in pipeline coatings.				
Features & Use	<ul style="list-style-type: none"> • Packaged in a polythene bag, divided by a plastic clip, and sealed in an aluminium foil pack • For small area repairs to most types of pipe coatings, including FBE, 3LPE, 3LPP and polyurethanes • Outstanding mechanical properties and rapid cure characteristics together with excellent adhesion to most pipe coating materials. 				
Approvals/ Certification	<ul style="list-style-type: none"> • Meets the requirements of GBE/CW6 Part 1 for External Pipe Protection • BS6920 Factory and site application and WRAS water fittings directory • Meets the performance requirements of BS EN 10290 and AWWA C222 • Malaysian SPAN approved 				
Finish	Sheen				
Volume Solids	100%				
VOC Content	0 g/litre				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Typical	0.5 mm	0.5 mm	0.07 m ² /pack	
	Typical	5 mm	5 mm	0.007 m ² /pack	
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated				
Drying Times	Applied to 1 mm DFT	+10°C	+20°C	+30°C	+40°C
	Dust Free	40 min	15 min	5 min	3 min
	Hard Dry	1½ hr	40 min	20 min	5 min
	Overcoating	40 min	15 min	5 min	3 min
	Full Cure	7 days	6 days	5 days	4 days
	Drying and recoating times are related to the surface temperature				
Colours	Beige				
Mix Ratio/ Product Code	10ATP Base 3 parts by volume Hardener 1 part by volume				
Pot Life	approx. 5 min at 25°C				
SG	1.31 kg/lit mixed				
Storage Conditions	Store in dry, cool conditions and protect from frost				
Shelf Life	Minimum 48 months if stored as above in unopened containers				
Flash Point	Above 60°C				

Acothane Twin Pack Repair Kit

<p>Surface Preparation</p>	<ul style="list-style-type: none"> All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams Steel: blast clean to minimum Sa2½ (ISO 8501-1:2007), surface profile depth 75-100µm. Mechanical tools may also be used providing a profile of minimum 75µm. <u>Do not polish the steel surface</u> Overlap onto existing Acothane coating: remove any loose material to establish a firm edge. Feather sound coating and abrade surface to provide a key. Thoroughly abrade to remove gloss, surface contaminants etc. by suitable method (sweep blasting, abrasive disk grinding etc.) Concrete: remove all laitance and other contaminants by most appropriate methods. Ensure the concrete is dry to a reading of <16% on the Wood Moisture Equivalent (WME) scale. Prime with Acothane LV Sealer 				
<p>Mixing</p>	<p>Remove outer foil wrapper. Remove plastic clip. Mix the contents of the pack by thoroughly working the components in the plastic bag together for at least 2 minutes. Remove corner of bag and dispense. See Acothane Twin Pack Mixing Instructions</p>				
<p>Thinner</p>	<p>Do not thin Equipment Cleaner No.4 Thinner</p>				
<p>Application Conditions</p>	<p>Do not apply when rain, mist, sleet or snow are imminent. Normal application requires relative humidity below 80%. To avoid risk of condensation, application should be performed only when the steel surface temperature is at least 3°C (5°F) above the dew point. Application at temperatures below 1°C (33°F) must be carefully monitored, since the possible presence of ice on the surface (or in pores, in the case of concrete) will result in poor performance.</p>				
<p>Application Methods</p>	<p>Method</p>	<p>Airless Spray</p>	<p>Conventional Spray</p>	<p>Brush</p>	<p>Roller</p>
<p style="text-align: center;">See below</p>					
<ul style="list-style-type: none"> Use plastic divider or spatula to apply 					
<p>Product Notes</p>	<ul style="list-style-type: none"> Activator contains isocyanates – refer to Safety Data Sheet In-service temperature limits: Wet – 0°C to 70°C depending on solution; Dry – minus 20°C to + 120°C continuous In order to comply with WRAS certification, a minimum cure time of 14 days at 7°C is required before contact with drinking water Overcoating - abrading will be required if overcoating after 24 hours Acothane Twin Pack has excellent adhesion to abraded Fusion Bonded Epoxy (FBE), and suitably prepared 3LPE and 3LPP. Please consult Axalta Coating Systems for technical advice 				
<p>Health & Safety</p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.</p>				

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.