

TECHNICAL DATA SHEET

TDS: TMW488
349/W488

ACRYLIC ROOF DRESSING

DESCRIPTION:

Teamac Acrylic Roof Dressing is a fast drying, water based coating that dries to a low sheen finish.

RECOMMENDED USE:

Teamac Acrylic Roof Dressing is used to protect, refresh and decorate tile and brick roofs as well as sealing asbestos sheets and barns.

AVAILABILITY:

5 litre

FINISH:

Matt

COLOUR:

Red, Grey, Green

TYPICAL S.G. (SPECIFIC GRAVITY):

1.15 to 1.28 @ 20 °C

VOLUME SOLIDS:

31 to 37%

WET FILM THICKNESS W.F.T

85 microns

DRY FILM THICKNESS D.F.T

30 microns

EXPECTED SPREADING RATE:

7 to 12 sq.m / litre

@ 30 microns D.F.T depending on porosity.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

3.0 Poise @ 25 °C

FLASH POINT:

Non-flammable

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 2 hours @ 20 °C

Hard dry: 12 hours @ 20 °C

Full hardness: 3 to 5 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours or Overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

41 max g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application Do not apply below 10 °C. restrictions

Method: Brush or Roller

Thinner Clean Water
(Max vol): (10%)

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning solvent: Water

Recoat 12 hours or
interval: Overnight

SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

ACRYLIC ROOF DRESSING**349/W488**

grease, oil and any other contaminants.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

Do not apply below 10 °C. Cold and damp conditions will prolong drying times. As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

N/A

SUBSEQUENT COAT:

Teamac Acrylic Roof Dressing

REMARKS:**HEALTH AND SAFETY:**

See safety data sheet - SDS 10642

ISSUED:

14 April 2014

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 320194.

For further advice contact Teamac Technical Services on +44(0)1482 320194

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMAC

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266

Email: info@teamac.co.uk

www.teamac.co.uk